



Canadian Association  
of Physicists

Association canadienne  
des physiciens et physiciennes

Contribution ID: 3282

Type: Oral (Non-Student) / Orale (non-étudiant(e))

## A scanning tunneling microscopy study of a two dimensional organometallic network on the Ag(111) surface

Thursday, 9 June 2022 12:00 (15 minutes)

Self-assembly is one of the most important bottom-up fabrication strategies to produce two-dimensional (2-d) networks at solid surfaces. Driven by an intricate equilibrium between molecule–molecule and molecule–substrate interactions, these interactions can be used to generate stable extended 2-d geometric structures. For example, halogen-terminated molecules can be activated on surfaces to form 2-d  $\pi$ -conjugated polymers [1].

In this work we focus on a particular class of 2-d nanomaterials in which metal atoms are incorporated into the molecular layer. The structures are characterized by organometallic coordination, i.e. C-metal-C linkage, between adjacent molecules. These materials are predicted to exhibit novel properties, i.e. topological insulators, superconductivity, and other exotic quantum phases [2].

We study the adsorption of a tribromo-substituted heterotriangulene molecule (TBTANGO [1]) on the Ag(111) surface using room temperature scanning tunneling microscopy (STM) in ultrahigh vacuum. We find that deposition of TBTANGO molecules onto a substrate held at elevated substrate temperatures ( $\sim 240^\circ\text{C}$ ) yields a high quality extended porous two-dimensional molecular network of TANGO molecules with organometallic C-Ag-C linkage. Each pore consists of six dehalogenated molecules and the honeycomb network can be characterized by a hexagonal unit cell with a lattice constant of  $19.8 \pm 0.5 \text{ \AA}$ . Within error, the overlayer is commensurate with the silver substrate ( $\sim 7a_{\text{Ag}}$ ). In addition, the molecular overlayer exhibits a single orientation, indicating it is aligned with the high symmetry directions of the underlying substrate.

At monolayer coverage, most of the surface is covered by the honeycomb network (80%), however adjacent to silver atomic steps we observe a novel compact molecular phase. This phase is characterized by a hexagonal unit cell with a lattice parameter of  $\sim 9.1 \text{ \AA}$ . STM images are consistent with C-metal-C linkage, however in the compact phase the Ag atom/cluster is linked to 3 TANGO molecules. To our knowledge this bonding motif has not been observed previously in similar 2-d organometallic networks.

[1] Galeotti *et al.*; Nature Materials **19**, 874–880 (2020).

[2] Dong *et al.*; Prog. in Surf. Sci. **91**, 101-135 (2016).

**Primary author:** Mr MARCHESE, Davide (Lakehead University)

**Co-author:** GALLAGHER, Mark

**Presenter:** GALLAGHER, Mark

**Session Classification:** R2-5 Materials Synthesis and Characterization (DCMMP) | Synthèse et caractérisation de matériaux (DPMCM)

**Track Classification:** Technical Sessions / Sessions techniques: Condensed Matter and Materials Physics / Physique de la matière condensée et matériaux (DCMMP-DPMCM)