

Two-Dimensional Temperature Measurements of Nanocrystalline Diamond Stripper Foils at SNS

A. Oguz, W. Blokland, N. Evans, K. Ewald

*Spallation Neutron Source, Oak Ridge National Laboratory,
Oak Ridge, TN, USA*

HB2023, CERN, Geneva, Switzerland

Oct. 11, 2023

ORNL is managed by UT-Battelle, LLC for the US Department of Energy


Outline

- Motivation
 - Spallation Neutron Source
 - Nanocrystalline Stripper Foils at SNS
 - Foil Heating & Material Property Change
- Foil Temperature Measurement System
 - Two-Color Pyrometry
 - Optical System Configurations
 - System Calibration
- Experimental Results
 - Temporal Measurements with Integrating Pyrometer
 - Imaging Pyrometer Configurations
 - Spatial Temperature Profile with Imaging Pyrometer
 - Time Resolved Temperature Profiles
- Summary

The Spallation Neutron Source



Front-End:
Produce the H⁻ beam pulse





LINAC: Accelerates the beam to 1.0 GeV, ~90% speed of light

After Upgrade:
1.3 GeV, 2.8 MW

Injection Foil:
Strip H⁻ to protons




Accumulator Ring: Compress the beam pulse 1 ms → 700 ns, after 1000 turns @60 Hz






Liquid Hg Target:
Neutrons are liberated, cooled and delivered

- **1 GeV, 1.7 MW** proton beam for producing neutrons (2.8 MW @1.3 GeV after upgrade)
- H⁻ Multi-Turn Charge-Exchange Injection to create a short pulse of protons in the Ring
- **1.8×10^{14} protons/pulse** in the Ring
- **Beam power limiting factors:**
 - Injection foil survivability; Beam loss





Nanocrystalline Diamond Foils at SNS

- Foils are nanocrystalline diamond grown on Si substrates.
 - Thickness: 250 – 400 $\mu\text{g}/\text{cm}^2$ (or 1 – 2 μm).
- SNS overcame early years of foil issues that limited beam power.
- R&D partnership with Center for Nanophase Material Science (CNMS) on foil production & characterization
- Foil corrugation method developed
 - Thermal expansion mismatch (diamond vs. silicon)
 - Grain size uniformity: residual stress changes during conditioning
- SNS effort:
 - Foil characterization: Foil Test Stand
 - Study foil behavior: Foil flutter, Holes, Curling, Buckling, Tearing
 - Foil Temperature Measurements







SEM Analysis of Nanocrystalline Diamond Foil Nucleation Processes



Foil Heating & Material Property Change

- Power deposited in the foil cause **heating**, **beam loss** and **material changes**.
- Energy deposited causes material change:
 - **nanocrystalline diamond** → **polycrystalline graphite**
 - **Increase in emissivity** ($\epsilon_{\text{diamond}} < \epsilon_{\text{graphite}}$)
 - Reduces foil heating (thermal conductivity increases)
- Foils have two major limitations:
 - Radiation Damage (beam loss, scattered particles hit beam pipe cause radiation)
 - **Sublimation** (Thinning, crystal lattice destruction, mechanical deformation)
- There is a practical beam power density limit for foil use.
- Calculation must be verified by measurements to estimate lifetime of foil for power upgrade at 2.8 MW.



(Y. Takeda & M. Plum, IPAC 2013)


(S. Lebedev & A. Lebedev, PRSTAB 2008)

Two-Color Pyrometry



- Need only two wavelengths and based on the ratios of the measurements with calibration constants σ_i and σ_j to extract the temperature values.
- Do not need to know emissivity **as long as two wavelengths are close enough to cancel in the ratio.**
- Foil temperature range (1000 – 2100K), required to work 1.0 – 2.5 μm region.
- **Challenges:**
 - High radiation (~10Rad/hour, highest radiation area in accelerator).
 - **Limited Accessibility:** Restricts placing our instrument closer to the foil area.
 - Total optical path length: ~40m, usable aperture size: ~ \varnothing 100mm.

Planck's Law:

$$I(\lambda, \epsilon, T) = \frac{2hc^2}{\lambda^5} \frac{\epsilon(\lambda)}{e^{\frac{hc}{\lambda kT}} - 1}$$



Distribution of Blackbody Spectrum



Ratio of Two-Color Measurement:



$$R_{i,j} = \frac{\sigma_i I(\lambda_i, \epsilon(\lambda_i), T)}{\sigma_j I(\lambda_j, \epsilon(\lambda_j), T)} = \frac{\sigma_i \lambda_i \epsilon(\lambda_i)}{\sigma_j \lambda_j \epsilon(\lambda_j)} e^{\frac{2hc^2}{T} \left(\frac{1}{\lambda_j} - \frac{1}{\lambda_i} \right)}$$

Temperature:




$$T = \frac{2hc^2 \left[\left(\frac{1}{\lambda_i} \right) - \left(\frac{1}{\lambda_j} \right) \right]}{\ln R_{i,j} - 5 \ln \left(\frac{\lambda_i}{\lambda_j} \right)}$$

Optical System Configurations

- Integrated Optical System:
 - Ø4.0" Cassegrain, f/10, EFL = 1010 mm, BFL = 180 mm, Coating: protected. Ag, 0.4 µm–20 µm.
 - Image sampling pinhole mirror size: Ø50 µm.
 - Dichroic beam splitter, 36 mm x 25 mm.
 - High throughput bandpass filters (1072nm & 1300nm, T>0.95), Ø1.0".
 - Two photodiode based integrating pyrometer.
- Pinhole mirror to allow spatial sampling of beam spot on foil, reduces background light, therefore measurement uncertainties.





System Calibration with Blackbody Source (1000 – 2000K)



Foil Temperature Temporal Measurements

- Algorithm for obtaining T_{max} , T_{min} and τ_c (colling constant):
 - Calculated for 1 second time interval, *i.e.* averaged over 60 pulses, using fit routine.




Ratio:
$$R = \frac{V_1(t) - V_{1o}}{V_2(t) - V_{2o}}$$

Fit function to extract cooling constant:

$$T(t) = \frac{T_{max}}{1 - e^{-\frac{f}{\tau_{cool}}}} \left[e^{-\frac{\text{mod}(t-t_0, f)}{\tau_{cool}}} - e^{-\frac{f}{\tau_{cool}}} \right] + T_{min}$$

Calibration Equation:
$$T = 248.34R^2 + 1804.1R + 587.03$$



Foil Temperature vs. Beam Power (2022)









TABLE II. Averaged peak (T_{max}) and minimum (T_{min}) temperature and cooling constant (τ_c) as well as associated RMS values of Foil#2 and Foil#6 under various beam power settings.



P_b (kW)	T_{max} (K)	T_{min} (K)	τ_c (ms)
Foil#2:			
615	1490.9 ± 3.5	1301.6 ± 5.5	22.5 ± 0.2
720	1561.9 ± 10.7	1301.5 ± 21.6	19.9 ± 0.9
829	1604.3 ± 14.2	1318.0 ± 19.2	19.0 ± 0.7
927	1650.7 ± 2.9	1335.7 ± 18.5	18.4 ± 0.6
Foil#6:			
805	1291.8 ± 6.9	988.6 ± 20.4	14.5 ± 0.7
905	1332.4 ± 8.6	988.9 ± 16.1	13.8 ± 0.6
1000	1384.3 ± 5.8	1004.9 ± 10.3	13.5 ± 0.3
1105	1427.0 ± 7.7	998.9 ± 12.4	12.8 ± 0.3
1201	1477.2 ± 12.7	1002.9 ± 20.2	12.4 ± 0.5
1315	1547.9 ± 7.6	998.6 ± 9.5	11.7 ± 0.2
1398	1589.9 ± 17.1	1016.0 ± 20.9	11.7 ± 0.3

- Unconditioned foil (Foil#2) heats up quickly as compared to old foil (Foil#6)
 - Diamond to graphitization process still ongoing ($\epsilon_{diamond} < \epsilon_{graphite}$)
 - Lower emissivity means less ability to release the heat (or radiative cooling)
- Cooling constant:
 - Longer time to cool for new foil (Foil#2) than old foil (Foil#6)
 - Higher beam power speeds up graphitization process (shorter cooling time)







Two-Color Imaging Pyrometer (2023)

- Ø8.0", EFL=2.4m, Cassegrain telescope
 - Increased light collection efficiency
 - Increased resolution
- Spatio-Temporal (**2D+1D**) measurement
 - **Spatial 2D**: SWIR Cameras
 - **Temporal 1D**: Photodiodes
- Improved SNR
 - High throughput filters ($\Delta\lambda = 70\text{nm}$, $T = 0.98$)
 - Smaller detectors ($\text{Ø}3.0\text{ mm} \rightarrow \text{Ø}0.3\text{ mm}$)
- Two independent systems work side-by-side




System CAD model





System Optical Specs


SWIR Camera: Allied Vision Goldeye G-033 TEC1




Photodiode: Hamamatsu G10899-003K





Imaging Resolution Test w/
3.0"x3.0" USAF Target @40m



Magnification: 0.0625






Specs	
Resolution	640 (H) x 512 (V)
Spectral Range	900 – 1700 nm
Sensor Type	InGaAs
Pixel Size	15 μm x 15 μm
Max. Frame Rate at Full Res.	301 fps
ADC	14 bit
Cooling Temperature	5 $^{\circ}\text{C}$
Image Buffer (RAM)	256 MB
Dark Current	110 ke^-/s (20 $^{\circ}\text{C}$)






Imaging Pyrometer Calibration with Blackbody Source

- Blackbody source:
 - 0.1 °C stability, emissivity: 0.999 (0.6 – 2.0 μm)
- Measured:
 - SWIR camera 2D array ratio signal
 - Photodiode ratio signal with pinhole size: Ø100μm
 - Distance: 40 m



Calibration process: ratios of image intensities at two-wavelengths measured at respective blackbody temperature


Visible Camera Image: blackbody image sampled through pinhole (Ø100μm)




Calibration Setup in Foil Lab at SNS (2023)

Temperature Profile






Temperature vs. H⁻ beam power



Temperature vs. time @1.4MW



Time-Resolved Temperature Profile



Summary

- Designed, built & calibrated two-color imaging pyrometer with a wide working range (900 – 2000K).
- We have spatio-temporal measurements of foil temperature at various H⁻ beam power (0.6 – 1.7MW).
 - First-hand temperature map of stripper foils under high-intensity beams have been obtained.
 - Temporal evolution of temperature profile obtained.
- Developed an effective & reliable data analysis algorithm to extract foil temperature.
 - Foil cooling constant shows good correlation with beam power & foil conditioning status.
 - Would offer more insight on foil graphitization process under different beam conditions.
- Temperature measurement uncertainties:
 - Integrating pyrometer: ± 15 K
 - Imaging pyrometer: TBD
- 2D Pyrometer Status:
 - Data is still being analyzed.
 - Optimization of filter choices will be next (SNR in shorter wavelength can be improved).
 - Thorough calibration and more studies will follow.