

**Last (43rd) RD50 Workshop on
Radiation Hard
Semiconductor Devices for
Very High Luminosity
Colliders (CERN)**



Report of Contributions

Contribution ID: 63

Type: **not specified**

Thermal Annealing of Electron, Neutron and Proton Irradiation Effects on SiC Radiation Detectors

Wednesday, 29 November 2023 09:20 (20 minutes)

Silicon carbide (SiC) is a wide bandgap semiconductor with physical properties that make it especially appropriate for radiation monitoring in radiation-harsh environments and for elevated temperature operation. In this work, the radiation effects in electron, neutron and proton irradiated 4H-SiC pn junction diodes have been investigated by means of electrical characterization in both, reverse and forward polarizations, including current-voltage characteristics measured in the temperature range from -50°C to +200°C. It is found that the observed radiation-induced conduction resistance is exponentially dependent with the measuring temperature. The generation of acceptor-like defects is thought to be responsible for the resistivity increase of the material, eventually leading to the formation of a semi-insulating layer, with loss of diode rectification character. The stability of the radiation-induced effects has been evaluated by applying series of thermal treatments up to 400°C. Interestingly for applications, partial recovery of diode rectification functionality is observed for electron irradiated devices, with a diode conduction recovery of more than four orders of magnitude. Furthermore, partial recovery of detectors charge collection efficiency (CCE) in alpha particle detection is registered on all cases, electron, neutron or proton irradiated devices, once subjected to the applied thermal treatments.

Additionally, it is observed that the limited conduction registered under forward bias for highly irradiated SiC diodes actually allows their application as radiation detectors when operated in forward polarization. Although some lower CCE is found for SiC detectors under forward bias, better energy resolution is obtained under this operation regime, particularly at low absolute bias voltages. It is thought that filled radiation-induced traps under forward bias condition decrease charge trapping of electron-hole pairs generated upon exposure to an alpha particles source.

Briefing, some superior characteristics of SiC devices, such as those involving operation at high temperature values, may enable their use beyond the intrinsic limitations of silicon devices. Furthermore, they may help simplify some current radiation detectors experiments implemented with silicon devices, in which cooling is needed to keep functional operation after high irradiation fluences or exposure to visible light must be prevented.

Primary authors: Dr RAFÍ, Joan Marc (Instituto de Microelectrónica de Barcelona, CNM-CSIC); Dr PELLEGRINI, Giulio (Instituto de Microelectrónica de Barcelona, CNM-CSIC); Prof. GODIGNON, Philippe (Instituto de Microelectrónica de Barcelona, CNM-CSIC); Dr RIUS, Gemma (Instituto de Microelectrónica de Barcelona, CNM-CSIC); Mr DAUDERYS, Vainius (Instituto de Microelectrónica de Barcelona, CNM-CSIC); Dr TSUNODA, Isao (National Institute of Technology (KOSEN), Kumamoto College); Dr YONEOKA, Masashi (National Institute of Technology (KOSEN), Kumamoto College); Dr TAKAKURA, Kenichiro (National Institute of Technology (KOSEN), Kumamoto College); Dr KRAMBERGER, Gregor (Jozef Stefan Institute); Dr MOLL, Michael (European Organization for Nuclear Research (CERN))

Presenter: Dr RAFÍ, Joan Marc (Instituto de Microelectrónica de Barcelona, CNM-CSIC)

Session Classification: SiC

Contribution ID: 64

Type: **not specified**

Four-quadrant Si and SiC Photodiodes for Beam Position and Monitor Applications

Wednesday, 29 November 2023 09:00 (20 minutes)

Single and four-quadrant (4Q) photodiodes are very common beam intensity and position diagnostic devices for hard X-ray synchrotron beamlines, and they are also of interest for real time monitoring and dosimetry in particle therapy medical applications. Ultrathin Si devices are advantageous in terms of cost and sensing area compared to diamond standard. X-ray beam position monitors, are to be thinner than 10 μm when made of silicon to achieve X-ray transmission higher than 90% for photon energies above 10 keV. Owing to their lower dark current, lower susceptibility to temperature and visible light conditions, and potential radiation hardness, there is also interest in silicon carbide (SiC) for some of these applications.

In this work, an extensive study involving physical and electrical characterization, as well as radiation effects, is carried out on single and 4Q photodiodes fabricated on ultrathin (10 μm , 5 μm and 3 μm) Si films from Silicon-on-Insulator (SOI) substrates, as well as on 1-2 μm -thick Si membranes obtained by chemical back-etching of high resistivity (HR) Float Zone (FZ) bulk Si substrates. Furthermore, 4Q devices fabricated on 5 μm -thick semi-insulating SiC epitaxial layers on bulk 4H-SiC substrates are also studied. Finally, the performance of the devices as radiation detectors is investigated by means of laser beam scanning transient current technique (TCT) and X-ray test beam at XALOC beamline of ALBA Synchrotron in Cerdanyola del Vallès (Barcelona).

Primary authors: Dr RAFÍ, Joan Marc (Instituto de Microelectrónica de Barcelona, CNM-CSIC); Dr QUIRION, David (Instituto de Microelectrónica de Barcelona, CNM-CSIC); Ms DUCH, Marta (Instituto de Microelectrónica de Barcelona, CNM-CSIC); Dr LOPEZ PAZ, Ivan (Instituto de Microelectrónica de Barcelona, CNM-CSIC); Mr DAUDERYS, Vainius (Instituto de Microelectrónica de Barcelona, CNM-CSIC); Mr CLAUS, Tobias (Instituto de Microelectrónica de Barcelona, CNM-CSIC); Dr FLETA, Celeste (Instituto de Microelectrónica de Barcelona, CNM-CSIC); Mr BRAVO, Javier (Instituto de Microelectrónica de Barcelona, CNM-CSIC); Dr MOFFAT, Neil (Instituto de Microelectrónica de Barcelona, CNM-CSIC); Mr MOLAS, Bernat (ALBA Synchrotron); Dr BOER, Roeland (ALBA Synchrotron); Dr JUAN-HUIX, Judith (ALBA Synchrotron); Dr TSUNODA, Isao (National Institute of Technology (KOSEN), Kumamoto College); Dr YONEOKA, Masashi (National Institute of Technology (KOSEN), Kumamoto College); Dr TAKAKURA, Kenichiro (National Institute of Technology (KOSEN), Kumamoto College); Dr KRAMBERGER, Gregor (Jozef Stefan Institute); Dr MOLL, Michael (European Organization for Nuclear Research (CERN)); Prof. GODIGNON, Philippe (Instituto de Microelectrónica de Barcelona, CNM-CSIC); Dr PELLEGRINI, Giulio (Instituto de Microelectrónica de Barcelona, CNM-CSIC)

Presenter: Dr RAFÍ, Joan Marc (Instituto de Microelectrónica de Barcelona, CNM-CSIC)

Session Classification: SiC

Contribution ID: 65

Type: **not specified**

A lightweight algorithm to model Radiation Damage Effects in Monte Carlo Events for High-Luminosity LHC experiments

Wednesday, 29 November 2023 11:50 (20 minutes)

Radiation damage significantly impacts the performance of silicon tracking detectors in Large Hadron Collider (LHC) experiments such as ATLAS and CMS, with signal reduction being the most critical effect. While adjusting sensor bias voltage and detection thresholds can help mitigate these effects, generating simulated data that accurately mirrors the performance evolution with the accumulation of luminosity, hence fluence, is crucial.

The ATLAS and CMS collaborations have developed and implemented algorithms to correct simulated Monte Carlo (MC) events for radiation damage effects, achieving impressive agreement between collision data and simulated events.

In preparation for the high-luminosity phase (HL-LHC), the demand for a faster ATLAS MC production algorithm becomes imperative due to escalating collision rates, events, tracks, and hits, imposing strict constraints on available computing resources. This talk outlines the philosophy behind the new algorithm, its implementation strategy, and the essential components involved. The presentation also includes results from closure tests.

Primary author: NAKKALIL, Keerthi (APC,CNRS/IN2P3 and Université de Paris)

Co-author: BOMBEN, Marco (APC & Université Paris Cité, Paris (FR))

Presenter: NAKKALIL, Keerthi (APC,CNRS/IN2P3 and Université de Paris)

Session Classification: Radiation damage general

Contribution ID: 66

Type: **not specified**

MAPS devices with internal gain for timing applications: state of the art and future developments

Thursday, 30 November 2023 09:00 (20 minutes)

In this contribution we present an update about the development of Monolithic Active Pixel Sensors (MAPS) at INFN in the framework of the ARCADIA project. Thanks to the first two engineering runs, manufactured in 2020 and 2021 with a 110 nm CMOS process, the device concept has been well assessed and tested, both through extensive laboratory characterizations and the comparison between experimental measurements and numerical simulations. In view of timing applications, a multiplication layer has been added to the design of our third run, delivered in early 2023. Here we present the first electrical and dynamic characterization campaigns performed on the passive test structures, which proved that the sensors (i) can be depleted and (ii) properly operate in the charge multiplication regime. Finally, also a few key aspects of the sensor optimization in perspective of the incoming productions will be considered through the discussion of combined TCAD-Montecarlo numerical analyses.

Primary author: Dr MANDURRINO, Marco (INFN Torino (IT))

Presenter: Dr MANDURRINO, Marco (INFN Torino (IT))

Session Classification: LGAD

Contribution ID: 67

Type: **not specified**

18 MeV Proton Irradiation of Low Gain Avalanche Detectors

Thursday, 30 November 2023 11:20 (20 minutes)

The LGAD technology is of great interest for high-energy physics (HEPs) as a 4-D tracking device and has been qualified for use in the timing detectors of the CMS and ATLAS experiments for the high luminosity upgrade of the LHC (HL-LHC). During the operation in strong radiation fields, the radiation damage progressively leads to performance degradation of LGADs, which therefore need a more profound theoretical understanding and further design optimizations.

The following study presents the results of 18 MeV proton irradiation conducted at the cyclotron of the Bern University Hospital. The investigation of radiation-induced degradation produced by low energy protons is of special interest since it demonstrates the limits of the Non-Ionizing Energy Loss (NIEL) scaling. LGADs produced by Hamamatsu Photonics (HPK) as well as devices with differently carbonated gain layers produced by Centro Nacional de Microelectrónica (CNM)-IMB are included in the study.

Electrical characterization, radiation-induced acceptor removal and gain reduction as well as timing measurements of a selected subset of samples will be presented. In addition, an outlook with comparison to similar devices irradiated at CERN with 23 GeV protons will be discussed.

Primary author: KRAUS, Veronika (Vienna University of Technology (AT))

Co-authors: FERNANDEZ GARCIA, Marcos (Universidad de Cantabria and CSIC (ES)); MOLL, Michael (CERN); MOBIUS, Silke (Universitaet Bern (CH))

Presenter: KRAUS, Veronika (Vienna University of Technology (AT))

Session Classification: LGAD

Contribution ID: **68**

Type: **not specified**

Hunting for Sharks with TCAD (Simulation of TPA-TCT measurements on LGAD Gain Suppression)

Wednesday, 29 November 2023 14:00 (20 minutes)

We present TCAD simulations on the gain suppression in LGAD sensors as measured with TPA-TCT.

Primary authors: CURRAS RIVERA, Esteban (EPFL - Ecole Polytechnique Federale Lausanne (CH)); FERNANDEZ GARCIA, Marcos (Universidad de Cantabria and CSIC (ES)); MOLL, Michael (CERN); WIEHE, Moritz (CERN); PAPE, Sebastian (Technische Universitaet Dortmund (DE))

Presenter: MOLL, Michael (CERN)

Session Classification: Radiation damage general

Contribution ID: 69

Type: **not specified**

Two Photon Absorption –Transient Current Technique: TCAD Simulation of a PIN & Influence of Radiation Damage on the TPA-TCT

Wednesday, 29 November 2023 14:20 (20 minutes)

The Two Photon Absorption –Transient Current Technique (TPA-TCT) is a tool for the characterisation of particle detectors. Contrary to present state of the art TCT, TPA-TCT enables characterisation measurements with three dimensional spatial resolution. A tabletop setup for the investigation of silicon based detectors was commissioned at CERN to pioneer the technique. A 430 fs pulse fiber laser with a wavelength of 1550 nm is used, to generate excess charge by Two Photon Absorption in silicon. The laser light is focused so that excess charge is generated in a small volume (approximately $1\mu\text{m} \times 1\mu\text{m} \times 20\mu\text{m}$) around the focal point. This talk presents the TPA-TCT setup at CERN SSD and shows recent investigation of radiation damage in 150 μm thick planar sensors fabricated by CIS. The beam depletion due to linear absorption and the influence on the refractive index are investigated. Furthermore, TCAD simulation are used to study TPA-TCT measurements in a PIN diode.

Primary author: PAPE, Sebastian (Technische Universitaet Dortmund (DE))

Co-authors: WIEHE, Moritz (CERN); MOLL, Michael (CERN); FERNANDEZ GARCIA, Marcos (Universidad de Cantabria and CSIC (ES))

Presenter: PAPE, Sebastian (Technische Universitaet Dortmund (DE))

Session Classification: Radiation damage general

Contribution ID: 70

Type: **not specified**

Defect Spectroscopy on Proton Irradiated 4H Silicon Carbide Devices

Wednesday, 29 November 2023 09:40 (20 minutes)

New radiation hard materials are investigated for future high energy particle physics experiments. Silicon carbide is one of the materials currently considered, due to its interesting properties, e.g. a larger bandgap and a higher breakdown field compared to silicon. The larger bandgap leads to low leakage currents even after high fluences of irradiation, allowing for non-cooled operation. This study focuses on investigating intrinsic and radiation-induced defects in n-type 4H-SiC devices by subjecting them to 23 GeV protons at various fluences. The sensors studied were manufactured by IMB-CNM, with a 5 μm or 50 μm thick epitaxial layer on top of a 350 μm thick 4H-SiC substrate. The samples were irradiated at IRRAD to $1\text{E}+11$, $1\text{E}+12$, $1\text{E}+13$, $1\text{E}+14$ and $1\text{E}+15$ p/cm². TSC and DLTS measurements were performed in the temperature range of 20 K to 350 K. The presented results include IV and CV measurements taken before and after irradiation, as well as the defect parameters obtained from TSC and DLTS measurements.

Primary author: SORGENFREI, Niels (Albert Ludwigs Universitaet Freiburg (DE))

Co-authors: ARNQVIST, Elias; RIZWAN, Faiza (Career break fellow); MOLL, Michael (CERN); WIEHE, Moritz (CERN); GURIMSKAYA, Yana

Presenter: SORGENFREI, Niels (Albert Ludwigs Universitaet Freiburg (DE))

Session Classification: SiC

Contribution ID: 71

Type: **not specified**

Characterisation of the FBK EXFLU1 thin sensors with gain in a high fluence environment

Thursday, 30 November 2023 10:00 (20 minutes)

The EXFLU1 batch of LGAD sensors on substrates of thickness between 15 and 45 μm were exposed to various radiation grades between 1×10^{-14} and $5 \times 10^{-15} \text{ n}_{\text{eq}}\text{cm}^{-2}$ using the neutron reactor at JSI. The sensor designs themselves, manufactured at FBK, are optimised to preserve characteristics at high fluences. The latest studies of the effects of radiation have been performed, with the impact on thin sensors of varying design considered for their characterisation pre- and post-irradiation, and are presented.

Primary authors: FONDACCI, Alessandro (INFN Perugia (IT)); MOROZZI, Arianna (INFN, Perugia (IT)); HANNA, Cecilia (Universita e INFN Torino (IT)); PASSERI, Daniele (University & INFN, Perugia (IT)); MOSCATELLI, Francesco (IOM-CNR and INFN, Perugia (IT)); BORGHI, Giacomo (Fondazione Bruno Kessler); PATERNOSTER, Giovanni (Fondazione Bruno Kessler); LANTERI, Leonardo (Universita e INFN Torino (IT)); MENZIO, Luca (Universita e INFN Torino (IT)); COSTA, Marco (Universita e INFN Torino (IT)); FERRERO, Marco (Universita e INFN Torino (IT)); CENTIS VIGNALI, Matteo (FBK); BOSCARDIN, Maurizio (FBK Trento); PASTRONE, Nadia (Universita e INFN Torino (IT)); CARTIGLIA, Nicolo (INFN Torino (IT)); WHITE, Robert Stephen (Universita e INFN Torino (IT)); ARCIDIACONO, Roberta (Universita e INFN Torino (IT)); MULARGIA, Roberto (University & INFN Turin (IT)); GIORDANENGO, Simona (Istituto Nazionale di Fisica Nucleare); CROCI, Tommaso; SOLA, Valentina (Universita e INFN Torino (IT))

Presenter: WHITE, Robert Stephen (Universita e INFN Torino (IT))

Session Classification: LGAD

Contribution ID: 72

Type: **not specified**

Spatial resolution of RSD2 array of pixels measured at a beamtest

Thursday, 30 November 2023 10:20 (20 minutes)

This contribution presents the first study of the spatial resolution of an array of RSD2 450 um pitch pixels. The results have been obtained in the latest test beam at the DESY 6 GeV/c electron line. The readout board is based on the FAST2 ASIC, a 16-channel fast amplifier chip developed in Torino.

The results demonstrate that resistive readout yields a spatial resolution smaller than 5% of the pixel size and a 100% fill factor over an area covered by multiple pixels.

Primary author: CARTIGLIA, Nicolo (INFN Torino (IT))

Co-authors: SIVIERO, Federico (INFN - National Institute for Nuclear Physics); LANTERI, Leonardo (Universita e INFN Torino (IT)); MENZIO, Luca (Universita e INFN Torino (IT)); FERRERO, Marco (Universita e INFN Torino (IT)); WHITE, Robert Stephen (Universita e INFN Torino (IT)); ARCIDIACONO, Roberta (Universita e INFN Torino (IT)); MULARGIA, Roberto (University & INFN Turin (IT)); SOLA, Valentina (Universita e INFN Torino (IT))

Presenter: CARTIGLIA, Nicolo (INFN Torino (IT))

Session Classification: LGAD

Contribution ID: 73

Type: **not specified**

Time resolution of the RD50 HV CMOS MPW2

Tuesday, 28 November 2023 10:40 (20 minutes)

The CERN RD50 collaboration develops depleted monolithic active pixel CMOS sensors for future colliders with the aim of high radiation tolerance, good time resolution, and high granularity pixel detectors. We will show that one prototype in 150 nm high voltage CMOS from LFoundry, the RD50-MPW2, featuring 64 active pixels of 60 μm pitch has a time resolution of 220 ps for an injected charge of 12 ke-

Charge in the sensor was generated with laser pulses from the backside (back-TCT), where for each pixel the time of arrival and time over threshold were measured with a fast oscilloscope to evaluate the time resolution of the entire pixel circuit including in-pixel amplification and discrimination. This is compared to the timing performance of the analog circuitry through charge injection. This is the first time this measurement was performed for the entire pixel matrix. With a first two-dimensional in-pixel measurement in the pixel matrix plane, we give insight into the electric field in the sensor.

Primary authors: TSOLANTA, Christina (University of Oslo); NOBELS, Douwe Jesse Lars (Nikhef National institute for subatomic physics (NL)); SONNEVELD, Jory (Nikhef National institute for subatomic physics (NL)); KRAMER, Uwe (Nikhef National institute for subatomic physics (NL))

Presenter: SONNEVELD, Jory (Nikhef National institute for subatomic physics (NL))

Session Classification: Monolithic devices

Contribution ID: 74

Type: **not specified**

USTC-IME LGAD pre-production for HGTD

Thursday, 30 November 2023 09:20 (20 minutes)

The Low Gain Avalanche Detector (LGAD) technology is proposed for the ATLAS High Granularity Timing Detector (HGTD) towards the High-Luminosity Large Hadron Collider (HL-LHC). USTC-IME LGADs are designed by the University of Science and Technology of China (USTC) and fabricated by the Institute of Microelectronics of Chinese Academy of Science (IME, CAS). The prototypes of the USTC-ME LGAD are shown to meet the specifications of the HGTD project. The pre-production was launched in February 2023. The measurements of early series of this run will be presented.

Primary author: Mr ZHENG, Xiangxuan (University of Science and Technology of China (CN))

Presenter: Mr ZHENG, Xiangxuan (University of Science and Technology of China (CN))

Session Classification: LGAD

Contribution ID: 75

Type: **not specified**

Investigation of low gain avalanche detectors exposed to proton fluences beyond 10^{15} neq/cm²

Thursday, 30 November 2023 17:00 (20 minutes)

The High Luminosity Large Hadron Collider upgrade will increase the luminosity of the LHC by a factor of 10. Low gain avalanche detectors (LGADs) promise excellent timing resolution, which can mitigate the pileup associated with high luminosity. The most highly irradiated LGADs will be subject to 2.5×10^{15} neq/cm² of hadron fluence during Run 4; their timing performance must tolerate this. Hamamatsu Photonics K.K. (HPK) and Fondazione Bruno Kessler (FBK) LGADs have been irradiated with 400 and 500 MeV protons respectively up to the Run 4 hadron equivalent fluence. Measurements of the irradiated LGADs' leakage current, capacitance, charge collection, and timing performance are presented. A timing resolution better than 70 ps is observed for all fluences. Charge collection is below 10 fC for the HPK sensors after $(0.9 \pm 0.5) \cdot 10^{15}$ neq/cm², and for the FBK sensors after $(1.7 \pm 1.0) \cdot 10^{15}$ neq/cm² for all operating voltages below 600 V. 2x2 arrays of both the FBK and HPK LGADs were produced to study the inter-pad characteristics. The inter-pad resistance for the HPK LGADs stayed slightly above 10 M Ω for $5 \cdot 10^{14}$ neq/cm², and the inter-pad resistance of the FBK LGADs fell slightly below 1 M Ω after 10^{15} neq/cm². Observations of the punch-through voltage and inter-pad isolation for fast signals are reported.

Primary authors: SORENSON, Josef Daniel (University of New Mexico (US)); HOEFERKAMP, Martin (Department of Physics and Astronomy); KRAMBERGER, Gregor (Jozef Stefan Institute (SI)); SEIDEL, Sally (University of New Mexico / ATLAS); SI, Jiahe (University of New Mexico (US))

Presenter: SORENSON, Josef Daniel (University of New Mexico (US))

Session Classification: LGAD

Contribution ID: 76

Type: **not specified**

Radiation hardness studies of Half-Activated-Boron LGADs

Thursday, 30 November 2023 12:40 (20 minutes)

HPK has produced LGADs where boron was not fully activated after the implantation. This was an attempt to reduce acceptor removal in the gain layer by formation of defect complexes of non-activated interstitial boron atoms with radiation induced interstitial silicon atoms and other impurities. In this was the replacement of activated boron by interstitial silicon in the lattice position would be mitigated. A set of such sensors with different fraction of activated boron was irradiated by reactor neutrons and studied with CV-IV and charge collection/timing measurements.

Primary authors: HITI, Bojan (Jozef Stefan Institute (SI)); KRAMBERGER, Gregor (Jozef Stefan Institute (SI)); MANDIC, Igor (Jozef Stefan Institute (SI)); VELKOVSKA, Iskra (Jozef Stefan Institute (SI)); DEBEVC, Jernej (Jozef Stefan Institute (SI))

Presenters: KRAMBERGER, Gregor (Jozef Stefan Institute (SI)); VELKOVSKA, Iskra (Jozef Stefan Institute (SI))

Session Classification: LGAD

Contribution ID: 77

Type: **not specified**

Proton Hardness Factor at the Bonn Cyclotron Irradiation Site

Friday, 1 December 2023 12:00 (20 minutes)

The proton irradiation site at the Bonn Isochronous Cyclotron is in operation since 2021. The accelerator typically provides a 14 MeV (~12.5 MeV on DUT) proton beam with a few mm width and currents of 1 μA and to the site. DUTs are irradiated in a cooling box at < -20 °C, mounted on a XY-motorstage, which is moved row-wise through the beam on a grid-like pattern. Dedicated diagnostics enable online beam monitoring with relative uncertainties of a few %, allowing beam-driven irradiations, resulting in highly-precise and uniform fluence distributions. Cross-check measurements of the beam-based fluence determination method used in Bonn are compared to the typical (metallic) foil activation, yielding consistent results while the beam-based method has an uncertainty of a few %. Recent measurements of the proton hardness factor, using 150 μm thin, passive LFoundry sensors, yield a hardness factor of $\kappa = 3.74 \pm 0.12$, agreeing with the previous value with significantly lower uncertainty. Implications of the low-energy protons on the measured hardness factor and limitations for DUT irradiations in Bonn are discussed.

Primary author: WOLF, Pascal (University of Bonn (DE))

Co-author: DINGFELDER, Jochen Christian (University of Bonn (DE))

Presenter: WOLF, Pascal (University of Bonn (DE))

Session Classification: Facilities

Contribution ID: 78

Type: **not specified**

Effect of annealing on charge collection with n-on p type silicon strip detectors irradiated with 24 GeV/c protons

Wednesday, 29 November 2023 14:40 (20 minutes)

Extensive studies of effects of annealing at 60C on charge collection efficiency were made with miniature n in p type silicon strip detectors during development and production of sensors for ATLAS ITk strip detector. Measurements were made with Alibava system with electrons from Sr90 source with detectors irradiated with reactor neutrons and low energy protons. At not too high bias voltages typical annealing behavior was measured: beneficial effects of short term annealing was followed by a drop of charge collection efficiency at longer annealing times.

Recent measurements with detectors irradiated with 24 GeV protons in CERN IRRAD facility showed somewhat different behavior in which a drop of collected charge was observed after short term annealing. In this contribution first results of studies of this effect with charge collection and E-TCT measurements will be presented.

Primary authors: MANDIC, Igor (Jozef Stefan Institute (SI)); CINDRO, Vladimir (Jozef Stefan Institute (SI)); STRIP SENSOR COMMUNITY, ATLAS ITk

Presenter: MANDIC, Igor (Jozef Stefan Institute (SI))

Session Classification: Radiation damage general

Contribution ID: 79

Type: **not specified**

Charge Collection Study of SiC-LGAD - SICAR1

Wednesday, 29 November 2023 10:20 (20 minutes)

Silicon carbide (SiC) has potential to be used for fast particle detection in radiation environment because of its wider band gap and high electron mobility. To improve the SiC PIN detection for small signal generated by minimum ionizing particles (MIPs), a 4H-SiC Low Gain Avalanche Diode has been proposed –SICAR. The first version (SICAR1) has been fabricated with initial electrical test shows that the dark current is around 5.6uA under full depletion voltage at 350V. The charge collection efficiency is up to 98%@ 150V. These findings offer promising possibilities for fast particle detection in future radiation environments.

Primary author: SHI, Xin (Chinese Academy of Sciences (CN))

Presenter: SHI, Xin (Chinese Academy of Sciences (CN))

Session Classification: SiC

Contribution ID: **80**Type: **not specified**

Single Event Burnout in thin silicon sensors

Thursday, 30 November 2023 16:20 (20 minutes)

The Single Event Burnout (SEB) was observed for the first time in 50 μm -thick LGAD, and studied by ATLAS and CMS collaborations during the R&D activity on LGAD sensors for their respective timing detector.

The experimental results observed on particle beam showed that, in 50 μm -thick silicon sensors, the SEB occurs at bulk electric fields of 11.5-12 V/ μm .

In this contribution, we report SEB results recently obtained on silicon sensors with active thickness between 15 μm and 55 μm . Beam tests at DESY and CERN facilities, performed during the last year, showed a relationship between the active thickness of the sensor and the burnout electric field.

Primary author: FERRERO, Marco (Universita e INFN Torino (IT))

Co-authors: MOROZZI, Arianna (INFN, Perugia (IT)); SIVIERO, Federico (INFN - National Institute for Nuclear Physics); MOSCATELLI, Francesco (IOM-CNR and INFN, Perugia (IT)); LANTERI, Leonardo (Universita e INFN Torino (IT)); MENZIO, Luca (Universita e INFN Torino (IT)); CARTIGLIA, Nicolo (INFN Torino (IT)); ARCIDIACONO, Roberta (Universita e INFN Torino (IT)); MULARGIA, Roberto (University & INFN Turin (IT)); SOLA, Valentina (Universita e INFN Torino (IT))

Presenter: FERRERO, Marco (Universita e INFN Torino (IT))

Session Classification: LGAD

Contribution ID: 81

Type: **not specified**

Radiation resistance of Carbon-shield LGADs and comparison with standard carbonated LGADs

Thursday, 30 November 2023 16:40 (20 minutes)

LGAD sensors with a carbon-enriched multiplication layer are the state-of-the-art in terms of radiation resistance, concerning this specific sensor technology. The presence of carbon allows LGADs to operate, while maintaining unchanged temporal resolution, even after irradiation fluences of $1\text{-}2 \times 10^{15}$ neq/cm².

Carbonated LGADs have been successfully produced by FBK, CNM and IHEP-IEM. FBK, in EXFLU1 production, has recently produced LGADs with a carbon shield implanted below the gain layer, with the aim to protect the gain layer from bulk defect migration and to further improving their radiation resistance.

In this contribution, the first results obtained on Irradiated Carbon-shield LGADs are presented and compared with those of standard Carbonated LGADs.

Primary author: FERRERO, Marco (Universita e INFN Torino (IT))

Co-authors: FONDACCI, Alessandro (INFN Perugia (IT)); MOROZZI, Arianna (INFN, Perugia (IT)); HANNA, Cecilia (Universita e INFN Torino (IT)); PASSERI, Daniele (University & INFN, Perugia (IT)); MOSCATELLI, Francesco (IOM-CNR and INFN, Perugia (IT)); BORGHI, Giacomo (FBK - Fondazione Bruno Kessler (IT)); PATERNOSTER, Giovanni (FBK - Fondazione Bruno Kessler (IT)); LANTERI, Leonardo (Universita e INFN Torino (IT)); MENZIO, Luca (Universita e INFN Torino (IT)); COSTA, Marco (Universita e INFN Torino (IT)); CENTIS VIGNALI, Matteo (FBK); BOSCARDIN, Maurizio (FBK Trento); PASTRONE, Nadia (Universita e INFN Torino (IT)); CARTIGLIA, Nicolo (INFN Torino (IT)); WHITE, Robert Stephen (Universita e INFN Torino (IT)); ARCIDIACONO, Roberta (Universita e INFN Torino (IT)); MULARGIA, Roberto (University & INFN Turin (IT)); GIORDANENGO, Simona (Universita e INFN Torino (IT)); CROCI, Tommaso; SOLA, Valentina (Universita e INFN Torino (IT))

Presenter: FERRERO, Marco (Universita e INFN Torino (IT))

Session Classification: LGAD

Contribution ID: 82

Type: **not specified**

Measurements on last IMB-CNM LGADs production

Thursday, 30 November 2023 09:40 (20 minutes)

In this contribution we will present measurements on LGADs corresponding to our CNM's second production run based on 6-inch, 50 μ m active layer thick, Si-Si wafers (6LG2-v2 technology). The wafers were carbon enriched using five different implantation doses and one implantation energy. For the gain layer, samples were fabricated using a single boron implantation dose and energy. Measurements and analysis of the electrical characterization and radiation hardness were carried out on these LGADs.

Primary author: Mr VILLEGAS DOMINGUEZ, Jairo Antonio (IMB-CNM (CSIC))

Co-authors: Dr PELLEGRINI, Giulio (IMB-CNM (CSIC)); Mr MANOJLOVIC, Milos (IMB-CNM (CSIC)); Dr MOFFAT, Neil (IMB-CNM (CSIC)); Dr HIDALGO VILLENA, Salvador (IMB-CNM (CSIC))

Presenter: Mr VILLEGAS DOMINGUEZ, Jairo Antonio (IMB-CNM (CSIC))

Session Classification: LGAD

Contribution ID: 83

Type: **not specified**

Sensor design, guard ring, breakdown

Wednesday, 29 November 2023 12:30 (20 minutes)

Silicon pixel sensors manufactured using commercial CMOS processes are promising instruments for high-energy particle physics experiments due to their high yield and proven radiation hardness. As one of the essential factors for the operation of detectors, the breakdown performance of pixel sensors constitutes the upper limit of the operating voltage.

In the first part, we present a comparative study of six types of passive CMOS test structures fabricated on high-resistivity wafers, and each of them features a combination of different inter-pixel designs and sets of floating guard rings, which differ in the geometrical layout, implantation type, and overhang structure. The study based on the leakage current measurements of unirradiated samples and TCAD simulations was carried out to identify correlations between the guard ring designs and the breakdown voltages. This ultimately provide design features targeting higher breakdown voltages.

In the second part, we present the simulation study for improving the breakdown performance in the design of RD50-MPW4 monolithic CMOS detector prototype.

Primary author: ZHANG, Sinuo (University of Bonn (DE))

Presenter: ZHANG, Sinuo (University of Bonn (DE))

Session Classification: Radiation damage general

Contribution ID: 84

Type: **not specified**

Precision determination of the tracking resolution of beam telescopes

Friday, 1 December 2023 11:40 (20 minutes)

Beam tests are the standard method for determining the position resolution of detectors. This requires the precise knowledge of the beam-position resolution at the detector to be tested. A method is proposed which achieves this. It uses a segmented silicon detector with normally incident beam. It is found that for normal incidence events with cluster-size 2 have a position accuracy well below $1\ \mu\text{m}$. The method is first demonstrated with simulated events, which are also used to investigate how to deal with cross-talk, electronics noise, energetic β -electrons, and incident beams with a few degrees off the normal to the sensor plane. Finally, using CMS Phase-2 prototype pixel sensors before and after hadron irradiation, the accuracy of the beam tracks reconstructed by the EUDET beam telescopes of the DESYII test beam facility and extrapolated to the pixel sensor, is determined.

Primary author: KLANNER, Robert (Hamburg University (DE))

Co-authors: VAUTH, Annika (Universität Hamburg); GARUTTI, Erika (Hamburg University (DE)); STEINBRUECK, Georg (Hamburg University (DE)); Dr SCHWANDT, Joern (Hamburg University (DE)); EIKELMANN, Lukas; ANTONELLO, Massimiliano (Universität Hamburg)

Presenters: VAUTH, Annika (Universität Hamburg); Dr SCHWANDT, Joern (Hamburg University (DE))

Session Classification: Facilities

Contribution ID: 85

Type: **not specified**

Characterisation of the MC40 cyclotron irradiation line at the University of Birmingham

Friday, 1 December 2023 11:20 (20 minutes)

The MC40 cyclotron at the University of Birmingham is routinely involved with proton irradiations for several detector R&D projects. For the majority of these irradiations, a 27 MeV proton beam is delivered at a current of 200 nA, being able to supply fluences of a few 10^{15} n_{eq}/cm² in one day. The proton energy at the target and the corresponding hardness factor have been previously determined to be 24 MeV and 2.2, respectively. Following several maintenance works, a revision of the MC40 R&D irradiation line is important to assess the consistency in the performance since the last evaluation.

The two major focuses of the ongoing characterisation of the cyclotron is the dosimetry and an updated measure of the hardness factor. The proton dosimetry is performed using nickel foil and the beam energy incident on the foil is an important parameter given the energy dependant cross-section. To estimate this, a Geant4 simulation of the cyclotron irradiation line was established with the ability to profile the beam energy as it traverses the setup. Beam profile simulations is compared to measurements at the facility with gafchromic film. The hardness factor is determined via measurements of the leakage current in post-irradiated silicon diode structures.

Aside from understanding recent performance, these tests of the cyclotron also serve to better understand a recurring feature in ATLAS inner tracker (ITk) strip sensor test chips irradiated using the cyclotron. Specifically, the interstrip resistance of the interdigitated structures has consistently fallen under the quality assurance specifications. An investigation has been performed with test chips irradiated to fluence points in the range 1×10^{14} n_{eq}/cm² to 2×10^{15} n_{eq}/cm² at beam energies of 27 MeV and 20 MeV. The difference in beam energies provides a different TID per unit of proton fluence and the overall ratio of ionising to non-ionising damage delivered to the samples should differ significantly. The measurements of these interdigitated structures allows the interplay between ionising and non-ionising damage to be investigated.

Primary author: LIU, Eric (University of Birmingham (GB))

Co-authors: CHISHOLM, Andrew Stephen (University of Birmingham (GB)); GONELLA, Laura (University of Birmingham (UK))

Presenter: LIU, Eric (University of Birmingham (GB))

Session Classification: Facilities

Contribution ID: 86

Type: **not specified**

Charge carrier mobility evaluation in Silicon Microstrips detectors exploiting photoconductivity phenomena

Wednesday, 29 November 2023 11:30 (20 minutes)

Silicon Microstrips (STRIP) detectors were evaluated after 1MeV neutron irradiation in the fluence range from $1\text{E}+15$ to $1\text{E}+17$ /cm². Photoconductivity spectral measurements were performed in range from 0.45 eV to 3.5 eV of excitation energy with different applied electric potential. The spectral shape variation with the applied electric potential raised the idea of the model with changing quantum efficiency and the presence of the another mobility layer inside the samples. This is the extended research of the samples previously characterized by magnetoresistivity (MR) technique. The proposed model complements and better explains the MR results.

Primary author: MEKYS, Algirdas (Vilnius University)

Co-authors: Dr JURCIUKONIS, Darius (Vilnius University); Dr MOLL, Michael (CERN); Ms BALTA-SEVICIUTE, Paula (Vilnius University); Prof. VAITKUS, Juozas Vidmantis (Vilnius University)

Presenter: MEKYS, Algirdas (Vilnius University)

Session Classification: Radiation damage general

Contribution ID: 87

Type: **not specified**

Beam test characterization of RD50-MPW3

Tuesday, 28 November 2023 11:00 (20 minutes)

The RD50-MPW3 is a HV-CMOS sensor developed by the HV-CMOS working group manufactured in the LFoundry 150nm process.

In this talk, I will present the most recent testbeam results.

Following up on the results of the test beam in 2022 at the CERN-SPS facility, presented in earlier workshops, this talk focuses on the successful test beam campaign at DESY in Jul. 2023.

I will highlight the changes to the DAQ system, which led to improved results this year compared to earlier campaigns.

Furthermore, I will discuss the results gathered at the medical facility MedAustron in Austria.

At the end, an outlook to planned beam test campaigns in 2024 for the successor chip, the RD50-MPW4, will be presented.

Primary author: PILSL, Bernhard (Austrian Academy of Sciences (AT))

Presenter: PILSL, Bernhard (Austrian Academy of Sciences (AT))

Session Classification: Monolithic devices

Contribution ID: **88**Type: **not specified**

Electric field measurement in LGAD

Thursday, 30 November 2023 16:00 (20 minutes)

We propose a novel methodology to measure the electric field of LGAD. This method introduces the estimation of the elongation of the carrier cluster caused by diffusion and the divergence of the electric field force during its drift along the detector. The maximum of time derivative tested from edge-TCT is extracted to quantify the dispersion of the light-induced carriers. Both RASER simulation and experimental results have shown that the diffusion profile method could be applied to certain edge-TCT facilities as an alternative of electric field measurement.

Primary author: Ms XIAO, Suyu (Shandong Institute of Advanced Technology, China)

Presenter: Ms XIAO, Suyu (Shandong Institute of Advanced Technology, China)

Session Classification: LGAD

Contribution ID: 89

Type: **not specified**

The numerous configurations of „interstitial boron“ and their involvement in ARP of LGADs

Thursday, 30 November 2023 12:20 (20 minutes)

Authors: Kevin Lauer^{1,2}, Aaron Flötotto², Katharina Peh², Robin Müller², Wichard Beenken², Erich Runge², Dirk Schulze², Stefan Krischok², Thomas Ortlepp¹

Affiliations: 1 CiS Forschungsinstitut für Mikrosensorik GmbH, Erfurt, Germany
2 TU Ilmenau, Institut für Physik and Institut für Mikro- und Nanotechnologien, Ilmenau, Germany

Abstract: Defects in silicon are known to occur in numerous different configurations each exhibiting different properties e.g. related to the interaction with charge carriers. In this contribution recent results of density functional theory calculations of the so-called “boron interstitial (B_i)” defect in silicon are shown and compared to an already existing model of that defect. The “boron interstitial” defect means that a boron and a silicon atom share one lattice position. Configurations of that defect where the silicon interstitial atom is one or more lattice constants away from the boron atom are not considered. The acceptor removal phenomenon (ARP) which impacts low gain avalanche detectors (LGAD) is discussed on the basis of these recent results.

Primary author: LAUER, Kevin (CIS Institut fuer Mikrosensorik GmbH (DE))

Presenter: LAUER, Kevin (CIS Institut fuer Mikrosensorik GmbH (DE))

Session Classification: LGAD

Contribution ID: 90

Type: **not specified**

Timing Characterization of LGADs for Space Based Applications

Thursday, 30 November 2023 15:00 (20 minutes)

In modern astroparticle physics experiments, it is crucial to feature a tracker and a calorimeter to measure and identify primary charged cosmic rays; at the same time, it is necessary to distinguish those from the back scattered particles entering the tracker from the calorimeter. Time-of-flight measurements are also used for particle identification. In recent years, Low Gain Avalanche Detectors (LGADs) have emerged as a technological solution for precise timing measurements in the tens of ps range for High Energy Physics and other applications. In this field, the typical LGAD channel size is $O(1 \text{ mm}^2)$, whereas a silicon sensor for strip geometry in space application is 50-60 cm in length with 100-200 μm pitch, resulting in a channel area of about 1 cm^2 . This work presents the timing characterization of pad sensors with dimensions up to $1 \text{ cm} \times 1 \text{ cm}$ (with and without gain) using a picosecond infrared laser. Different sensor thicknesses are characterized to reduce the effect of capacitance on the timing performances. In addition to that, several gain structures are compared to find the best performing gain layer.

Primary authors: BISHT, Ashish (FBK); BOSCARDIN, Maurizio (FBK); CASO, Fabiola (UNITN); CAVAZZINI, Leo; CENTIS VIGNALI, Matteo (FBK); FICORELLA, Francesco (FBK); HAMMAD ALI, Omar; PATERNOSTER, Giovanni (FBK)

Presenter: CAVAZZINI, Leo

Session Classification: LGAD

Contribution ID: 91

Type: **not specified**

TCAD simulation of 4H silicon carbide LGADs

Wednesday, 29 November 2023 10:00 (20 minutes)

Silicon carbide (SiC) has several advantageous material properties, making it an appealing detector material: its high charge carrier saturation velocity and breakdown voltage allow for an intrinsically higher time resolution than for silicon (Si). The larger bandgap suppresses dark current, even for highly irradiated material, reducing power consumption and thus omitting the need for cooling.

However, current limitations in the manufacturing of epitaxial layers of sufficiently high resistivity and thickness, as well as its large ionization energy compared to Si, mitigate the number of generated charge carriers and therefore reduce the signal output. The realization of a 4H-SiC low gain avalanche diode (LGAD), utilizing a controlled charge multiplication, could overcome this drawback while simultaneously boosting time resolution.

This talk presents our progress in simulating and designing such 4H-SiC LGADs. It will review SYNOPSIS-TCAD simulations of simplified LGAD structures to benchmark and characterize crucial design parameters and impact ionization models. In addition, a simplified analytical model to expedite the search for viable designs will be introduced.

New Alpha and UV-TCT measurements of neutron-irradiated planar 4H-SiC diodes that indicate signal-enhancing properties when operated in forward bias will be shown and possible origins of this behavior will be discussed.

Finally, a status report of the previously presented 4H-SiC wafer run in collaboration with CNM will be given.

Primary author: GAGGL, Philipp (Austrian Academy of Sciences (AT))

Co-authors: GSPONER, Andreas (Austrian Academy of Sciences (AT)); BURIN, Jürgen (Austrian Academy of Sciences (AT)); WAID, Simon Emanuel (Austrian Academy of Sciences (AT)); BERGAUER, Thomas (Austrian Academy of Sciences (AT))

Presenter: GAGGL, Philipp (Austrian Academy of Sciences (AT))

Session Classification: SiC

Contribution ID: 92

Type: **not specified**

Test beam analysis of irradiated passive CMOS strip sensors

Wednesday, 29 November 2023 16:30 (20 minutes)

A significant challenge in producing the larger structures typical for silicon strip sensors is the limited reticle size of the CMOS process. This problem can be solved through the so called stitching of the reticles.

The sensors that are the subject of this talk are passive CMOS strip sensors, containing three different strip variants, designed by the University of Bonn. They were produced by LFoundry in a 150 nm process on a 3-5 k Ω cm float zone wafer, with additional backside processing by IZM Berlin. To examine the radiation hardness of the stitches, samples have been irradiated with reactor neutrons to various fluences up to $1 \cdot 10^{16}$ n_eq / cm². Possible effects of the stitching on spatial resolution, detection efficiency or charge collection efficiency and the general performance of the three designs have been studied in detail in several test beam campaigns at the DESY II test beam facility, where unirradiated as well as a number of irradiated CMOS strip sensors were thoroughly examined. In summary, we are able to demonstrate on a large number of samples that multiple stitching can be performed without any degradation of the sensor performance both before and after irradiation.

Primary authors: Mr SARI, Birkan (TU Dortmund); SPERLICH, Dennis (Albert Ludwigs Universitaet Freiburg (DE)); HUEGGING, Fabian (University of Bonn (DE)); LEX, Fabian Simon (Albert Ludwigs Universitaet Freiburg (DE)); GREGOR, Ingrid-Maria (DESY & Bonn University); ZATOCILOVA, Iveta (Albert Ludwigs Universitaet Freiburg (DE)); ARLING, Jan-Hendrik (Deutsches Elektronen-Synchrotron (DESY)); WEINGARTEN, Jens (Technische Universitaet Dortmund (DE)); JAKOBS, Karl (Albert Ludwigs Universitaet Freiburg (DE)); DIEHL, Leena (CERN); HAUSER, Marc (Albert Ludwigs Universitaet Freiburg (DE)); BASELGA, Marta (Technische Universitaet Dortmund (DE)); DAVIS, Naomi Afriyie (Deutsches Elektronen-Synchrotron (DE)); SORGENFREI, Niels (Albert Ludwigs Universitaet Freiburg (DE)); SPANNAGEL, Simon (Deutsches Elektronen-Synchrotron (DE)); ARGYROPOULOS, Spyros (Albert Ludwigs Universitaet Freiburg (DE)); MÄGDEFESSEL, Sven (University Freiburg); PARZEFALL, Ulrich (Albert Ludwigs Universitaet Freiburg (DE))

Presenter: LEX, Fabian Simon (Albert Ludwigs Universitaet Freiburg (DE))

Session Classification: Radiation damage general

Contribution ID: 93

Type: **not specified**

Development and characterisation of depleted monolithic active pixel sensors (DMAPS) in 150 nm and 180 nm CMOS technology

Tuesday, 28 November 2023 10:20 (20 minutes)

Monolithic active pixel sensors featuring depleted substrates (DMAPS) present a promising alternative for pixel tracker detectors operating in high-radiation and high-rate environments. The utilization of high-resistivity silicon substrates and high-voltage capabilities within commercial CMOS technologies holds the potential to significantly enhance radiation tolerance with respect to MAPS. TJ-Monopix2 and LF-Monopix2 chips are the most recent large-scale prototype chips in their respective development line with a column-drain readout architecture.

Designed in 150 nm LFoundry technology, LF-Monopix2 uses a large charge collection electrode with pixel electronics embedded in it. Benefits of this design are short drift paths and a homogeneous electric field across the sensor that increase the radiation tolerance. Optimization of the pixel layout minimizes potential coupling from the digital circuitry into the sensor node while reducing the pixel size to $50 \times 150 \text{ um}^2$ compared to its predecessor.

TJ-Monopix2 is designed in 180 nm Tower Semiconductor technology. Featuring a small charge collection electrode design with separate readout electronics, the pixel pitch of this sensor could be reduced to $33 \times 33 \text{ um}^2$. A small detector capacitance allows for a large signal-to-noise ratio while an additional n-type layer across the pixel ensures full depletion of the sensitive volume.

In this talk, an overview of both DMAPS developments including results from tests in laboratory and using a minimum ionising particle beam is given. For TJ-Monopix2, timing studies and charge collection measurements are highlighted. For LF-Monopix2, the performance after irradiation to fluences of up to $2e15 \text{ neq/cm}^2$ is shown.

Primary authors: BESPIN, Christian (University of Bonn (DE)); HUEGGING, Fabian (University of Bonn (DE)); KRUEGER, Hans (University of Bonn); CAICEDO SIERRA, Ivan Dario (University of Bonn (DE)); DINGFELDER, Jochen Christian (University of Bonn (DE)); SCHALL, Lars Philip (University of Bonn); WERMES, Norbert (University of Bonn (DE)); ZHANG, Sinuo (University of Bonn (DE)); HEMPEREK, Tomasz (University of Bonn (DE))

Presenters: HUEGGING, Fabian (University of Bonn (DE)); WERMES, Norbert (University of Bonn (DE))

Session Classification: Monolithic devices

Contribution ID: 94

Type: **not specified**

2D pixelated BNL AC-LGADs: From laser TCT to Test Beam characterization

Thursday, 30 November 2023 11:40 (20 minutes)

AC-LGAD (AC coupled Low-Gain Avalanche Detector) sensors have emerged as a highly promising technology for precision particle detection in collider experiments. These sensors offer exceptional capabilities, delivering remarkable time and spatial resolutions on the order of tens of micrometers and picoseconds, all while achieving a 100% fill factor. We present results obtained with AC-LGAD sensors developed by Brookhaven National Laboratory (BNL), showcasing their performance through measurements using infrared laser TCT and high energy particles at the CERN SPS test beam. We analyze and compare different machine learning algorithms, as well as the charge imbalance method, for the hit position reconstruction. In this study, square pixel sensor arrays with 500 μm pitch are presented, paving the way to study smaller pitch sensors in the near future for increased spatial resolution.

Primary authors: AIDAINNOVA WP6 TEST-BEAM GROUP; TRICOLI, Alessandro (Brookhaven National Laboratory (US)); MACCHIOLO, Anna (University of Zurich (CH)); KILMINSTER, Ben (University of Zurich (CH)); GIACOMINI, Gabriele (Brookhaven National Laboratory (US)); BARONE, Gaetano (Brown University); SENGER, Matias (University of Zurich (CH))

Presenter: SENGER, Matias (University of Zurich (CH))

Session Classification: LGAD

Contribution ID: 95

Type: **not specified**

First characterization of TI-LGAD technology in a test beam setup

Thursday, 30 November 2023 12:00 (20 minutes)

The Trench Isolated LGAD (TI-LGAD) technology offers a promising solution to LGAD's fill factor limitations, enabling small segmentation of fast timing silicon sensors for collider experiments. Previous laboratory studies with this technology have already shown similar timing performance and radiation hardness as for the LGAD technology, with a drastic improvement of the fill factor (reduction of inter-pixel no-gain distance). In this presentation we show the first results obtained with the TI-LGAD technology in a test beam setup with high energy particles. The evaluation of the inter-pixel distance in this regime will be presented, as well as the detection efficiency and time resolution. The new results are compared with previous laboratory measurements.

Primary authors: SENGER, Matias (University of Zurich (CH)); MACCHIOLO, Anna (University of Zurich (CH)); KILMINSTER, Ben (University of Zurich (CH)); BORGHI, Giacomo (Fondazione Bruno Kessler); PATERNOSTER, Giovanni (Fondazione Bruno Kessler); CENTIS VIGNALI, Matteo (FBK); BOSCARDIN, Maurizio (FBK Trento); AIDAINNOVA WP6 TEST-BEAM GROUP

Presenter: SENGER, Matias (University of Zurich (CH))

Session Classification: LGAD

Contribution ID: 96

Type: **not specified**

Radiation damage investigation of epitaxial p-type silicon for particle detectors using Schottky and pn-junction diodes

Wednesday, 29 November 2023 15:30 (20 minutes)

This project focuses on the investigation of trap energy levels introduced by radiation damage in epitaxial p-type silicon. Using 6-inch wafers of various boron doping concentrations ($1e13$, $1e14$, $1e15$, $1e16$, and $1e17$ cm^{-3}) with a $50\ \mu\text{m}$ epitaxial layer, multiple iterations of test structures consisting of Schottky and pn-junction diodes of different sizes and flavours are being fabricated at RAL and Carleton University.

In this talk, updates on the diode fabrication and electrical measurements of the structures will be given. The focus of this talk will be on the characterisation of trap parameters obtained from Deep-Level Transient Spectroscopy (DLTS) and supplemented by Thermally Stimulated Current (TSC) measurements. Spectra for unirradiated and neutron-irradiated diode samples will be shown and their details collected from Arrhenius analyses will be listed. Lastly, DLTS and Charge Collection Efficiency (CCE) measurements conducted on samples before and after neutron irradiation will be evaluated and their results compared.

Primary author: VILLANI, Enrico Giulio (Science and Technology Facilities Council STFC (GB))

Co-authors: KLEIN, Christoph Thomas (Carleton University (CA)); KOFFAS, Thomas (Carleton University (CA)); MCCORMICK, Angela (Carleton University (CA)); TARR, Garry (Carleton University (CA)); VANDUSEN, Robert (Carleton University (CA)); ZHANG, Dengfeng (University of Sheffield (GB)); PINTILIE, Ioana (National Inst. of Materials Physics (RO)); NITESCU, Andrei (National Institute of Material Physics -NIMP); WILSON, Fergus (Science and Technology Facilities Council STFC (GB)); ALLPORT, Philip Patrick (University of Birmingham (UK)); GONELLA, Laura (University of Birmingham (UK)); KOPSALIS, Ioannis (Austrian Academy of Sciences (AT)); MANDIC, Igor (Jozef Stefan Institute (SI)); CHEN, Yebo (Chinese Academy of Sciences (CN)); Dr KURTH, Matthew Glenn (Institute of High Energy Physics (CN)); LIU, Peilian (Chinese Academy of Sciences (CN))

Presenter: KLEIN, Christoph Thomas (Carleton University (CA))

Session Classification: Radiation damage general

Contribution ID: 97

Type: **not specified**

Radiation tolerance of 8-inch silicon sensors for CMS HGCAL

Wednesday, 29 November 2023 15:50 (20 minutes)

The High-Luminosity LHC will challenge the detectors with a nearly 10-fold increase in integrated luminosity compared to the previous LHC runs combined, thus the CMS detector will be upgraded to face the higher levels of radiation and the larger amounts of data collected. The High-Granularity Calorimeter (HGCAL) will replace the current endcap calorimeters of the CMS detector. It will facilitate the use of particle-flow calorimetry with its unprecedented transverse and longitudinal readout/trigger segmentation, with more than 6M readout channels. The electromagnetic section as well as the high-radiation regions of the hadronic section of the HGCAL (fluences above 10^{14} neq/cm²) will be equipped with silicon pad sensors, covering a total area of 620 m². Fluences up to 10^{16} neq/cm² and doses up to 1.5 MGy are expected. The sensors are processed on novel 8-inch p-type wafers with an active thickness of 300 μ m, 200 μ m and 120 μ m and cut into hexagonal shapes for optimal use of the wafer area and tiling. Each sensor contains several hundred individually read out cells of two sizes (around 0.5 cm² or 1.2 cm²). With each main sensor several small sized test structures are hosted on the wafers, used for quality assurance and radiation hardness tests. In order to investigate the radiation-induced bulk damage, the main sensors and single diodes from the test structures have been irradiated with neutrons at RINSC (Rhode Island Nuclear Science Centre, US) and JSI (Jožef Stefan Institute, Ljubljana, Slovenia) to fluences between $6.5 \cdot 10^{14}$ neq/cm² and $1.5 \cdot 10^{16}$ neq/cm². In this talk, the electrical characterisation and charge collection measurements of the irradiated silicon sensors will be presented. This includes first measurements with so-called partial sensors cut from multi-geometry wafers with internal dicing lines on the HV potential left in the active sensor area, the isothermal annealing behaviour of the bulk material and the CV-frequency and measurement-method dependence present in depletion voltage measurements in irradiated sensors. The observed behaviour of the electrical properties and charge collection efficiency is in agreement with the HGCAL specifications. The results are being used to optimize the HGCAL layout and to establish an operating and annealing scenario for HGCAL.

Primary author: KALUZINSKA, Oliwia Agnieszka (KIT - Karlsruhe Institute of Technology (DE))

Presenter: KALUZINSKA, Oliwia Agnieszka (KIT - Karlsruhe Institute of Technology (DE))

Session Classification: Radiation damage general

Contribution ID: 98

Type: **not specified**

Impact of environmental stresses on Low Gain Avalanche Diodes

Friday, 1 December 2023 09:40 (20 minutes)

Devices with internal gain, such as Low Gain Avalanche Diodes (LGADs) can have O(30) ps timing resolution. They play a crucial role in High Energy Physics (HEP) experiments. Similarly, resistive silicon devices, such as AC-coupled LGADs (AC-LGADs) sensors, achieve a fine spatial resolution while maintaining the LGAD's timing resolution. Devices of both types, with varying gain-layer width and doping characteristics, are produced at Brookhaven National Laboratory (BNL). However, their performance is strongly affected by environmental factors such as temperature, humidity, rapid changes in bias voltage settings, and storage conditions. For example, phonon scattering, which is strongly affected by temperature, plays a central role in avalanche multiplication at higher temperatures, where phonon scattering becomes prominent due to the temperature dependence of the phonon population. As such, the operating conditions, such as noise, gain and breakdown voltage, depend on these variables. In view of applications beyond the controlled environment of HEP experiments, these devices are stress-tested against varying environmental conditions. For example, the challenging operating conditions in outer space impose constraints on the operation performance, against temperature fluctuations. We study how different devices with different depletion layers and implantation characteristics respond to these changing climatic conditions. A systematic evaluation of the response of LGAD sensors as a function of these environmental parameters is therefore of essential importance when accounting for any application. This allows us to map the device performance back to the sensor's characteristics. In turn, this will allow the tailored fabrication of devices resilient to harsh conditions at no cost to the operational performance in controlled environments.

Primary authors: TRICOLI, Alessandro (Brookhaven National Laboratory (US)); BOYE, Diallo (Brookhaven National Laboratory); ROSSI, Enrico (Sezione di Pisa (IT)); D'AMEN, Gabriele (Brookhaven National Laboratory (US)); GIACOMINI, Gabriele (Brookhaven National Laboratory (US)); BARONE, Gaetano (Brown University (US)); ROLOFF, Jennifer (Brookhaven National Laboratory (US)); MOHAMED FAROOK, Mohamed Hijas (University of New Mexico (US)); MONDAL, Spandan (Brown University (US)); ELLIS, Spencer (Brown University (US)); RUSSELL, Trevor (Brown University (US)); CHEN, W (Brookhaven National Laboratory, Upton (NY), U.S.)

Presenter: BOYE, Diallo (Brookhaven National Laboratory)

Session Classification: LGAD

Contribution ID: 99

Type: **not specified**

Revealing distinct signals in inter-pad region of Ti-LGAD

Thursday, 30 November 2023 14:20 (20 minutes)

In this presentation, we continue our investigation of charge-space profiles in segmented LGADs with a focus on double-trenched LGADs (2Tr LGAD). We compare the signal behavior of the Ti-LGAD sample with double trenches in the interpad (IP) region to that of LGADs with 2p-stops and bias rings used as isolation structures (both types produced in the Ti-LGAD RD50 batch with difference that LGADs with 2p-stops and bias ring was used as reference prototype and only produced for comparison reasons).

Our experimental results revealed two distinct types of transient current signals in IP region of TI-LGAD: “normal” or “expected” signals resembling the pad signal, and “strong” signals with broadened waveforms and higher amplitudes. We analyze the occurrence of these signals in 2Tr LGADs through extensive acquisition.

We also identify “ghost” signals that randomly appear without laser illumination. The talk explores the dependence of signal characteristics on bias voltage and laser power at different temperatures and discusses potential explanations for the observed behavior.

Only results from study on double trenched prototype from wafer W11 are presented.

Primary authors: Prof. LASTOVICKA MEDIN, Gordana (University of Montenegro (ME)); Dr REBARZ, Mateusz (ELI Beamlines, ELI ERIC); Ms BACKOVIC, Vanja (University of Montenegro); Mr KARADZIC, Dejan (University of Montenegro)

Co-authors: Dr LASTOVICKA, Tomas (ELI Beamlines, ELI ERIC); Dr ANDREASSON, Jakob (ELI); Dr KRAMBERGER, Gregor (Jozef Stefan Institute)

Presenter: Prof. LASTOVICKA MEDIN, Gordana (University of Montenegro (ME))

Session Classification: LGAD

Contribution ID: 100

Type: **not specified**

Hunting for the ghost signals in Ti-LGADs

Thursday, 30 November 2023 14:40 (20 minutes)

We present the continuation of our research on IP signals in Ti-LGAD (Wafer 11). Our experimental examination on Ti-LGAD, from the wafer 11, revealed exceptionally high signals within the IP region, which was significantly higher than the signals measured in previously conducted experiments [1] on the segmented LGAD sample with two p-stops and a bias ring in the center of the IP region with the IPD=49 microns (from the same wafer: W11).

This time we show results from our extended research on larger pool of Ti-LGAD prototypes: from wafers W16 and W7. All sensors have 2 trenches in IP region, but the depths of trenches are different.

Tree types of signal in IP region: “expected” and “strong”, both induced by laser, and a few types of ghosts (wafer type correlated) are discussed. Special attention is given to the study of the rate of ghosts occurrences in all three samples from three different wafers. We studied also the occurrence rate ratio between the “strong” IP and the “normal” IP signal in pulse to pulse analysis in 10 000 single shot run experiment. Results are discussed.

[1] Gordana Laštovička-Medin, Mateusz Rebarz, Jovana Doknic, Ivona Bozovic, Gregor Kramberger, Tomáš Laštovička, and Jakob Andreasson. “Exploring the Interpad Gap Region in Ultra-Fast Silicon Detectors: Insights into Isolation Structure and Electric Field Effects on Charge Multiplication.” *Sensors* 23, no. 15 (2023): 6746.

Primary authors: LASTOVICKA-MEDIN, Gordana (University of Montenegro (ME)); Ms BACKOVIC, Vanja (University of Montenegro); Dr REBARZ, Mateusz (ELI Beamlines, ELI ERIC)

Co-authors: KARADZIC, Dejan (University of Montenegro); LASTOVICKA, Tomas (ELI Beamlines, ELI ERIC); Dr ANDREASSON, Jakob (ELI Beamlines, ELI ERIC); Dr KRAMBERGER, Gregor (Jozef Stefan Institute)

Presenter: LASTOVICKA-MEDIN, Gordana (University of Montenegro (ME))

Session Classification: LGAD

Contribution ID: **101**

Type: **not specified**

Test beam results from DMAPS produced in LF110 and TSI 180

Tuesday, 28 November 2023 11:20 (20 minutes)

The PSI HEP group has designed and produced test devices of DMAPS in two different technologies: Motic in LF 110 and TSI-R4S in TSI 180. The talk reports on the status of these projects including results from test beam campaigns at DESY.

Primary authors: ROHE, Tilman (Paul Scherrer Institute (CH)); EBRAHIMI, Aliakbar (Paul Scherrer Institute (CH)); BURKHALTER, Stephan Tobias (ETH Zurich (CH)); KAESTLI, Hans-Christian (Paul Scherrer Institute (CH)); MEIER, Beat (Paul Scherrer Institute (CH)); ERDMANN, Wolfram (Paul Scherrer Institute (CH))

Presenter: ROHE, Tilman (Paul Scherrer Institute (CH))

Session Classification: Monolithic devices

Contribution ID: 102

Type: **not specified**

Time resolution and field uniformity study of single cell 3D pixel structures neutron and proton irradiated up to $1 \times 10^{17} n_{eq}/cm^2$ at 120 GeV SPS beams

Wednesday, 29 November 2023 12:10 (20 minutes)

The proven radiation hardness of silicon 3D devices up to fluences of $1 \times 10^{17} n_{eq}/cm^2$ makes them an excellent choice for next generation trackers, providing $< 10 \mu m$ position resolution at a high multiplicity environment. The anticipated pile-up increase at HL-LHC conditions and beyond, requires the addition of < 50 ps per hit timing information to successfully resolve displaced and primary vertices. In this study, the timing performance, uniformity, and efficiency of neutron and proton irradiated single pixel 3D devices is investigated. Three different geometrical implementations are evaluated for fluences up to $1 \times 10^{17} n_{eq}/cm^2$ at 120 GeV SPS pion beams. The question of electronic bandwidth is also addressed, with respect to achievable time resolution, efficiency and collected charge. In such a tri-dimensional phase-space, an appropriate operating point is selected depending on the application requirements. A MIMOSA26 type telescope is used to provide detailed tracking information with a $\sim 5 \mu m$ position resolution. Productions with single- and double-sided processes, yielding active thickness of 130 and 230 μm respectively, are studied, with pixel sizes that vary from $55 \times 55 \mu m^2$ to $25 \times 100 \mu m^2$. A comparison of field uniformity with respect to electrode geometry is presented, as well as a time resolution study for incidence angles up to 12° .

Primary author: Dr GKOU GKOUSIS, Vagelis (University of Zurich)

Presenter: Dr GKOU GKOUSIS, Vagelis (University of Zurich)

Session Classification: Radiation damage general

Contribution ID: **103**Type: **not specified**

TCAD simulations of the ATLAS ITk-Strip sensors for the HL-LHC

Wednesday, 29 November 2023 16:10 (20 minutes)

The ATLAS ITk Strip detector is a planned tracker upgrade for the High-Luminosity LHC which utilizes n⁺-in-p silicon sensors fabricated by Hamamatsu Photonics with 300 μm signal-generation thickness and approximately 75 μm strip pitch. Measurements and simulations are presented for silicon strip sensors and test devices, including after irradiation to fluences up to 1.4*10¹⁵ 1-MeV neq/cm². Two-dimensional sensor simulations are developed with Sentaurus TCAD, informed using detailed optical and electrical measurements, and interfaced to AllPix² for detector simulations. Charge traps from the manufacturing process and from radiation-induced defects are studied, both through a parameterization of traps in the surface and bulk and by the direct measurement of traps using deep-level transient spectroscopy.

Primary authors: JESSIMAN, Callan (Carleton University (CA)); KLEIN, Christoph Thomas (Carleton University (CA)); DUVNJAK, Damir (Carleton University (CA)); Mr STAATS, Ezekiel (Carleton University (CA)); DANDOY, Jeff (Carleton University (CA)); KOFFAS, Thomas (Carleton University (CA))

Presenter: DANDOY, Jeff (Carleton University (CA))

Session Classification: Radiation damage general

Contribution ID: **104**

Type: **not specified**

Discussion: SiC

Wednesday, 29 November 2023 10:40 (20 minutes)

Presenter: BERGAUER, Thomas (Austrian Academy of Sciences (AT))

Session Classification: SiC

Contribution ID: **105**

Type: **not specified**

LGAD Discussion

Friday, 1 December 2023 10:20 (20 minutes)

Presenters: KRAMBERGER, Gregor (Jozef Stefan Institute (SI)); CARTIGLIA, Nicolo (INFN Torino (IT))

Session Classification: LGAD

Contribution ID: **106**

Type: **not specified**

How RD50 started

Tuesday, 28 November 2023 14:00 (20 minutes)

Presenter: BRUZZI, Mara

Session Classification: Goodbye RD50

Contribution ID: **107**

Type: **not specified**

History of the RD50 collaboration and Main Achievements

Tuesday, 28 November 2023 14:40 (30 minutes)

Presenter: MOLL, Michael (CERN)

Session Classification: Goodbye RD50

Contribution ID: **108**

Type: **not specified**

RD50 from Experiment perspective

Tuesday, 28 November 2023 14:20 (20 minutes)

Presenter: HARTMANN, Frank (KIT - Karlsruhe Institute of Technology (DE))

Session Classification: Goodbye RD50

Contribution ID: **109**

Type: **not specified**

p-type strip and pixel

Tuesday, 28 November 2023 15:10 (20 minutes)

Presenter: CASSE, Gianluigi (University of Liverpool (GB))

Session Classification: Goodbye RD50

Contribution ID: **110**

Type: **not specified**

3D detectors

Tuesday, 28 November 2023 15:30 (20 minutes)

Presenters: BOSCARDIN, Maurizio (Universita degli Studi di Trento and INFN (IT)); BOSCARDIN, Maurizio (FBK Trento)

Session Classification: Goodbye RD50

Contribution ID: **111**

Type: **not specified**

LGADs

Tuesday, 28 November 2023 15:50 (20 minutes)

Presenters: Dr PELLEGRINI, Giulio (Centro Nacional de Microelectrónica (IMB-CNM-CSIC) (ES)); Dr HIDALGO, Salvador (Instituto de Microelectronica de Barcelona (IMB-CNM-CSIC))

Session Classification: Goodbye RD50

Contribution ID: **112**

Type: **not specified**

Instrumentation

Tuesday, 28 November 2023 16:40 (20 minutes)

Presenter: FERNANDEZ GARCIA, Marcos (Universidad de Cantabria and CSIC (ES))

Session Classification: Goodbye RD50

Contribution ID: **113**

Type: **not specified**

Defects and Materials

Tuesday, 28 November 2023 17:00 (20 minutes)

Presenter: PINTILIE, Ioana (National Inst. of Materials Physics (RO))

Session Classification: Goodbye RD50

Contribution ID: **114**

Type: **not specified**

Simulation

Tuesday, 28 November 2023 17:20 (20 minutes)

Presenters: Dr SCHWANDT, Joern (Hamburg University (DE)); BOMBEN, Marco (APC & Université Paris Cité, Paris (FR))

Session Classification: Goodbye RD50

Contribution ID: **115**

Type: **not specified**

RD50 CMOS

Tuesday, 28 November 2023 17:40 (20 minutes)

Presenter: VILELLA FIGUERAS, Eva (University of Liverpool (GB))

Session Classification: Goodbye RD50

Contribution ID: **116**

Type: **not specified**

RD50 collaboration - Beyond scientific achievements

Tuesday, 28 November 2023 18:10 (20 minutes)

Presenter: KRAMBERGER, Gregor (Jozef Stefan Institute (SI))

Session Classification: Goodbye RD50

Contribution ID: 117

Type: **not specified**

Radiation Tolerance Study of CNM-IMB Run15973

Friday, 1 December 2023 10:00 (20 minutes)

We present the results of the Radiation Tolerance Study (Electrical and Radioactive Source characterization) performed at the IFCA on Carbonated-Enriched Gain-Layer small devices (single diode) from the Run #15973 production of CNM-IMB.

Primary authors: NAVARRETE RAMOS, Efren (Universidad de Cantabria and CSIC (ES)); Dr VILA ALVAREZ, Ivan (Instituto de Física de Cantabria (CSIC-UC)); GONZALEZ SANCHEZ, Javier (Universidad de Cantabria and CSIC (ES)); Dr DUARTE CAMPDERROS, Jordi (IFCA (UC-CSIC)); FERNANDEZ GARCIA, Marcos (Universidad de Cantabria and CSIC (ES)); JARAMILLO ECHEVERRIA, Richard (Universidad de Cantabria and CSIC (ES))

Presenters: NAVARRETE RAMOS, Efren (Universidad de Cantabria and CSIC (ES)); FERNANDEZ GARCIA, Marcos (Universidad de Cantabria and CSIC (ES))

Session Classification: LGAD

Contribution ID: 118

Type: **not specified**

Synchrotron light source X-ray detection with Low-Gain Avalanche Diodes

Friday, 1 December 2023 09:00 (20 minutes)

Low Gain Avalanche Diodes (LGADs) represent the state-of-art technology in fast timing measurement for charged minimum ionizing particles (MIPs). LGADs are initially developed for future Timing Detectors in the ATLAS and CMS experiments at the High-Luminosity LHC. One of LGADs'key features is the gradient-doped multiplication layer providing intrinsic gain. The intrinsic gain enables the detection of low energy X-rays with good energy resolution and precise timing capabilities. We extensively tested LGADs from HPK and BNL with varying thicknesses ranging from 20 μm to 50 μm at room temperature. These tests utilized X-ray energies from 5 keV to 70 keV at the Stanford Synchrotron Radiation Lightsource (SSRL) with 10ps pulsed X-ray bunches separated by 2ns interval. In this contribution, we will show that LGADs has better energy sensitivity and timing resolution for low energy X-ray than PiN devices under finely-tuned operational conditions. Moreover, we will demonstrate the high frame-rate capability of LGADs (with at least 500MHz). Additionally, we investigated the gain suppression effect resulting from point-like large charge deposition along with the aid of TCAD simulation. Lastly, we made a crude attempt to assess the feasibility of reliable Compton scattering detection with LGADs, which aim to employ LGADs as pass-through beam monitoring device for high-energy X-ray beams using Compton interaction.

Primary authors: SEIDEN, Abraham (University of California,Santa Cruz (US)); Prof. SCHUMM, Bruce Andrew (University of California,Santa Cruz (US)); SADROZINSKI, Hartmut (SCIPP, UC santa Cruz); SADROZINSKI, Hartmut (University of California,Santa Cruz (US)); Dr OTT, Jennifer (University of California,Santa Cruz (US)); Dr NIZAM, Mohammad (University of California Santa Cruz); Dr MAZZA, Simone Michele (University of California,Santa Cruz (US)); ZHAO, Yuzhan (University of California,Santa Cruz (US)); ZHAO, Yuzhan (University of California Santa Cruz)

Presenters: Dr OTT, Jennifer (University of California,Santa Cruz (US)); Dr MAZZA, Simone Michele (University of California,Santa Cruz (US))

Session Classification: LGAD

Contribution ID: 119

Type: **not specified**

Gain suppression studies at the CENPA tandem accelerator

Friday, 1 December 2023 09:20 (20 minutes)

PIONEER is a next-generation experiment proposed at the Paul Scherrer Institute to perform high precision measurements of rare pion decays. By improving the precision by an order of magnitude on the charged-pion branching ratio to electrons vs. muons and the pion beta decay, PIONEER will provide a pristine test of Lepton Flavour Universality and the Cabibbo angle anomaly. At the centre of the experiment, a high-granularity active target (ATAR) will stop the pion and characterise its decay. The ATAR is being designed to provide detailed 5D tracking information, allowing the separation of the energy deposits of the pion decay products in both position and time. The chosen technology is Low Gain Avalanche Detectors (LGAD). These are thin silicon detectors with moderate internal signal amplification. Several types of LGADs still under development are being evaluated to achieve a ~100% active region, such as AC-coupled LGADs (AC-LGADs) and Trench Insulated LGADs (TI-LGADs). Since a range of deposited charge from Minimum Ionizing Particle (MIP, few 10s of KeV) from positrons to several MeV from the stopping pions/muons is expected, the detection and separation of close-by hits in such a wide dynamic range will be the main challenge. Using the CENPA Tandem accelerator at the University of Washington, we studied the LGADs response of MeV-range deposits from a proton beam. This contribution will introduce the PIONEER experiment conceptual design and its physics case. The results of the test-beam study will also be presented.

Primary authors: SEIDEN, Abraham (University of California, Santa Cruz (US)); Prof. SCHUMM, Bruce Andrew (University of California, Santa Cruz (US)); SADROZINSKI, Hartmut (SCIPP, UC Santa Cruz); SADROZINSKI, Hartmut (University of California, Santa Cruz (US)); Dr OTT, Jennifer (University of California, Santa Cruz (US)); Dr NIZAM, Mohammad (University of California Santa Cruz); Dr MAZZA, Simone Michele (University of California, Santa Cruz (US)); ZHAO, Yuzhan (University of California Santa Cruz); ZHAO, Yuzhan (University of California, Santa Cruz (US))

Presenters: Dr OTT, Jennifer (University of California, Santa Cruz (US)); Dr MAZZA, Simone Michele (University of California, Santa Cruz (US))

Session Classification: LGAD

Contribution ID: **120**

Type: **not specified**

Discussion: Monolithic devices

Tuesday, 28 November 2023 11:40 (30 minutes)

Presenter: VILELLA FIGUERAS, Eva (University of Liverpool (GB))

Session Classification: Monolithic devices

Contribution ID: 121

Type: **not specified**

Discussion: Radiation damage

Wednesday, 29 November 2023 17:10 (20 minutes)

Presenters: CASSE, Gianluigi (University of Liverpool (GB)); PINTILIE, Ioana (National Inst. of Materials Physics (RO))

Session Classification: Radiation damage general

Contribution ID: **122**

Type: **not specified**

Discussion: Facilities

Friday, 1 December 2023 12:40 (20 minutes)

Session Classification: Facilities

Contribution ID: **123**

Type: **not specified**

Welcome to the 43rd RD50 Workshop

Tuesday, 28 November 2023 10:00 (20 minutes)

Presenter: MOLL, Michael (CERN)

Contribution ID: 124

Type: **not specified**

Towards the DRD3 collaboration

Thursday, 30 November 2023 17:20 (20 minutes)

Presenter: Dr PELLEGRINI, Giulio (Centro Nacional de Microelectrónica (IMB-CNM-CSIC) (ES))

Session Classification: LGAD

Contribution ID: 125

Type: **not specified**

Learning HISPANoS, a new neutron beam facility at CNA

Friday, 1 December 2023 12:20 (20 minutes)

We present the first detectors and Single Event Effects experiments in the new Hispanos neutron facility, located at the National Centre of Accelerators, Sevilla, Spain. The detector experiment tests commercial photodiodes, with special emphasis in how to avoid electromagnetic interference. The SEE experiment starts to characterize vulnerabilities of a Intel MAX10 FPGA under fast neutrons. Both tests and the lessons learned open way to more evolved experiments for particle detectors and SEE experiments using neutron beams.

Primary authors: C. VILAS BÓAS, Alexis (Universidade de São Paulo (BR)); FERNÁNDEZ MARTÍNEZ, Begoña (Universidad de Sevilla (ES)); GUERRERO SANCHEZ, Carlos (Universidad de Sevilla (ES)); SOLDADO, Caterina (Aalto University); PALOMO PINTO, Francisco Rogelio (Universidad de Sevilla (ES)); JIMÉNEZ SÁNCHEZ, Jorge (School of Engineering at Universidad de Sevilla (ES)); ASCAZUBI, Ricardo (Intel Corp.)

Presenter: PALOMO PINTO, Francisco Rogelio (Universidad de Sevilla (ES))

Session Classification: Facilities

Contribution ID: 126

Type: **not specified**

Developments of GaN Schottky devices at NRC

Wednesday, 29 November 2023 16:50 (20 minutes)

Wide-bandgap semiconductors such as gallium nitride (GaN) have inherent advantages based on their material properties such as high critical field, high electron mobility and most importantly, high bond energies that lead to lower displacement damage, all of which imply a high radiation hardness. This material system should therefore be considered as an alternative to silicon-based detectors for next-generation colliders. Here, we report on preliminary results of Schottky devices composed of 8 μm thick GaN epitaxially grown with no intentional doping on n+ GaN substrates using Hydride Vapor Phase Epitaxy (supplied by Kyma) and fabricated at NRC Canada. Capacitance measurements reveal low background carrier concentrations $\sim 1\text{E}15\text{ cm}^{-3}$ and average pixel capacitance of 3 nF/cm². Dark currents of devices with various areas, including guard rings, provide evidence of bulk dominated leakage currents. After rapid thermal anneal treatment dark currents of $\leq 5\text{ nA/cm}^2$ for reverse bias of -1 V were observed. The barrier height of the Schottky contact was extracted using forward biased conditions at room temperature and estimated to be 0.7-0.75 eV, in reasonable agreement with literature data of Ni/GaN barriers although with some inhomogeneity. Devices were also subjected to reverse biases of 200 V with no breakdown behaviour. Preliminary light injection measurements were performed using a focused laser at 355 nm with a spot size of 10 μm adjacent to a 1 mm diameter device. Although carrier collection was observed, it is too early to quantitatively assess the carrier collection efficiency. Furthermore, no strong dependency on bias was observed. Further processing development is planned using NTT's GaN epi on GaN substrates grown by MOCVD.

Primary authors: WALKER, Alexandre (National Research Council of Canada); VILLANI, Enrico Giulio (Science and Technology Facilities Council STFC (GB)); NOEL, Jean-Paul (National Research Council of Canada); Dr GRIFFIN, Ryan (National Research Council); KOFFAS, Thomas (Carleton University (CA))

Presenter: WALKER, Alexandre (National Research Council of Canada)

Session Classification: Radiation damage general

Contribution ID: 127

Type: **not specified**

Greetings from special guests via zoom

Tuesday, 28 November 2023 18:00 (10 minutes)

Presenters: VERBITSKAYA, Elena (Ioffe Institute (RU)); Prof. LINDSTROEM, Gunnar (Hamburg University); Prof. VAITKUS, Juozas (Vilnius University (LT))

Session Classification: Goodbye RD50

Contribution ID: **128**

Type: **not specified**

Special greetings

Tuesday, 28 November 2023 16:10 (5 minutes)

Presenter: LINDSTRÖM, Gunnar (Hamburg University)

Session Classification: Goodbye RD50

Contribution ID: **129**

Type: **not specified**

Goodbye

Friday, 1 December 2023 13:00 (5 minutes)

Presenter: MOLL, Michael (CERN)