

Pinning Mechanisms, Lengthwise Fluctuations, and
Flux Jumps in REBCO Coated Conductors:
A Torque Magnetometry Study up to $B = 45$ T

Jan Jaroszynski
CMS/DC Field user support



NSF/DMR-1644779 and 2128556
PIs: Gregory Boebinger
and Kathleen Amm



If you are interested we can help:

- CFS
 - NHMFL 40 T
 - NHMFL LittleBigCoil
 - AMPeers/UT Houston
 - HTSI
 - SuperPower
 - Faraday (as SuperOx)
-
- Shanghai
 - Fujikura
 - Tokamak Energy
 - Proxima
 - UKIFS
 - Type One Energy
 - and others approaching

NHMFL users

NHMFL user program:

This four month period (Jan-May)

9 weeks of magnet time in 31 T resistive magnet for REBCO CC, mainly torque


Next application deadline:

March 21st


jaroszy@magnet.fsu.edu




Torque magnetometer



screening currents,
=> magnetic moment m






$$m \propto I_c$$
$$\vec{\tau} = \vec{m} \times \vec{B}$$
$$T = \tau/R + W + F$$



PPMS version





5 - 45 T measurements: no change in trend




45 T hybrid magnet



vs. T: exponential, stretched exponential around the ab plane



Weak and strong pinning separation



there is no shortage of options for fitting I_c !

Z. Chen et al. 2009



Weak and strong pinning:

Multi component fits:

$$I_c(B, T, \theta) = \frac{a_1(B, T)}{\omega_1^2(B, T) \sin^2(\theta) + 1} + \frac{a_2(B, T)}{\omega_2^2(B, T) \sin^2(\theta) + 1}$$

$$a_1(B, T) = a_{11}(T) \exp(-B/B_0)$$


strong

$$a_1(B, T) = a_{11}(B) \exp[-(T/T_+)^2]$$

$$a_2(B, T) = a_{21}(T) B^{-\alpha}$$

weak

$$a_2(B, T) = a_{21}(B) \exp[-T/T_0]$$





=> N.M. Strickland et al. 2022, N.J. Long et al. 2013




More weak pinning in recent production!

weak/strong pinning ratios in old/new production:



All modern samples: low anisotropy ~5

MORE WEAK PINNING





1. 15 % BZO R&D
- 2-4 typical modern production
(Shanghai, FF, SuperPower)
- 5-6 SuperPower: old AP and no BZO

Low (~ 5) anisotropy and wide peak
are typical nowadays: more weak pinning




Strong pinning can be modified:



G. Bradford PhD thesis, heat treatment:



Lengthwise I_c variations: strong pinning mainly




- large variations at the ab plane (strong pinning)
- stronger at edge slit
- different slitting? 2-4-4-2

4-4-4



2-4-4-2





Force/torque reel-to-reel magnetometer at $T=20\text{ K}$ $B=5\text{ T}$

- no clear correspondence between 77 K and low T




Like eddy current brakes




Patent pending



Flux jumps in thick samples



single sample:
rotation in field



60 sample stack
Field sweep

T. Grag et al. IEEE TAS 35 (2025)

Many thanks:



Anca-Monia
Constantinescu
2014-2017, 2022



Aixia Xu
2007-2012
2021->



Valeria Braccini
2009-2010



Ashleigh Francis
2020-2023

Griffin Bradford, Jun Lu, Rastislav Ries
George Miller, Tim Murphy, and David Larbalestier

NHMFL User Collaboration Grants Program

- Fast fatigue and current assessment in REBCO coated conductors
- Advancing lengthwise assessment of REBCO tapes using force magnetometry



NSF/DMR-1644779 and 2128556
PI: Gregory Boebinger and Kathleen Amm



SUMMARY

- torque magnetometry: massive angular $I_c(B,T,\theta)$ characterization
- phenomenology of angular I_c at low T becomes quite clear
- in modern samples weak pinning dominates=> low anisotropy
- lengthwise fluctuation: at the edges, mainly strong pinning at ab
- heat treatment modifies anisotropy and lengthwise changes
- flux jumps observed in thick REBCO films

