



Contribution ID: 153

Type: POSTER

Magnetic and Electric Properties of Cadmium Films Containing Nanometer Size Clusters of Iron

Abstract

Are you a student, a delegate from developing countries or a participant with physical needs and would like to apply for a sponsored accomodation. Please answer with yes or no.

yes

Please specify whether you would prefer an oral or poster contribution.

poster

Summary

Dilute magnetic impurities in non-magnetic metallic matrices have been intensively studied in for investigating single ion Kondo effect and the development of spin glassy behavior upon increasing magnetic interactions with dopant concentration. Here we report on an investigation of magnetic iron nano-clusters formed in non magnetic hosts with low solubility for iron. We will concentrate on films of cadmium in comparison with our earlier studies on silver films. Nanometer size clusters of iron can be formed in films containing iron in the range from 0.1 to several at% via vapor co-deposition. Characterization of samples was performed via X-ray diffraction, resistivity, magnetization, susceptibility, and Mössbauer spectroscopic measurements at various temperatures and applied magnetic fields. Up to concentrations of about 2 at% Fe the iron clusters are well defined as distinguished from their distinct hyperfine parameters.

Spin-freezing is traced from Mössbauer and magnetization data with freezing temperatures ranging from below 4 K up to about 15 K depending on cluster concentration. Models for describing the dynamic hyperfine spectra in this temperature range will be presented taking into account different mechanisms for cluster-cluster interactions.

Above the freezing temperature we can derive average cluster magnetic moments from magnetization data and also from the field dependence of the magnetic hyperfine fields at Fe obtained in applied external fields. Both macroscopic and local magnetic data are in good agreement yielding moments on the order of 15-20 μB for iron clusters in Cd films, compared with 35-40 μB found for Ag films. I.e., in both cases the clusters comprise only few atoms. The hyperfine spectra taken in applied field indicate a reduction of the iron moments at low temperatures which can be interpreted with moment compensation via conduction electron scattering. A competition between Kondo effect and the magnetic coupling of clusters via conduction electron polarization interaction could be clearly traced from the resistivity data of the silver films.

Whereas in films with iron concentrations up to about 2 at% we have controlled formation and growth of small clusters, this is no more the case for higher concentrations. Strong irreversibility in magnetization is found extending up to 100 K. The hyperfine data prove the presence of the same kinds of clusters as found for lower concentration yet with much bigger sizes.

Author: Mr TRUJILLO, Wiliam (Brazilian Center for Research in Physics (CBPF))

Co-authors: Prof. BAGGIO-SAITOVITCH, Elisa (Brazilian Center for Research in Physics (CBPF)); Prof. LITTERST, F. Jochen (IPKM, TU Braunschweig); Dr MUNAYCO, Pablo (Brazilian Center for Research in Physics (CBPF))

Presenter: Mr TRUJILLO, Wiliam (Brazilian Center for Research in Physics (CBPF))

Track Classification: Magnetism and Magnetic materials - Bulk and thin layers