

Characterization of $\text{Ce}_{1-x}\text{Pr}_x\text{O}_2$ was Synthesized by a Co-precipitate Method.

Thursday, May 21, 2015 1:00 PM (3h 30m)

$\text{Ce}_{1-x}\text{Pr}_x\text{O}_2$ ($x = 0, 5, 10, 15$ and 20) was synthesized by a co-precipitate method. The crystallization temperature started around 300°C . After calcination at 800°C for 8 hr, the grains size of undoped sample was about 69 nm. Doping Pr into CeO_2 resulted-in the reduction to grains size. The smallest grains size of 40 nm was observed for $\text{Ce}_{0.8}\text{Pr}_{0.2}\text{O}_2$. Incorporation of Pr into ceria lattice was confirmed from the increased in lattice parameter and oxygen vacancy. Moreover the area intensity ratio of ceria main peak over the vacancy peak was reduced with the increasing dopant. $\text{Ce}_{0.8}\text{Pr}_{0.2}\text{O}_2$ have the highest conductivity of 0.01 S/cm above 600°C .

Primary author: Mr NGIEWLAY, Pilan (Department of Material Science and Nanotechnology, Faculty of Science, Khon Kaen University, Khon Kaen, THAILAND 40002)

Co-author: Dr TANGTRAKARN, Apishok (Department of Physics, Faculty of Science, Khon Kaen University, Khon Kaen, THAILAND 40002)

Presenter: Mr NGIEWLAY, Pilan (Department of Material Science and Nanotechnology, Faculty of Science, Khon Kaen University, Khon Kaen, THAILAND 40002)

Session Classification: Poster-3

Track Classification: Material Physics, Nanoscale Physics and Nanotechnology