

Luminescent properties of Cesium Hafnium Chloride scintillators doped with alkaline earth metals

Thursday, 21 September 2017 10:33 (1 minute)

High-energy-resolution scintillators are demanded for food/environmental gamma-ray monitoring systems in Fukushima or for other applications. Generally, halide scintillators have high light output due to small band-gap energy, and therefore high energy resolutions are expected [1]. However, almost all halide materials have hygroscopic nature, which makes them difficult to handle.

In 2015, Cs_2HfCl_6 (CHC) has been reported as non-hygroscopic halide scintillator [2]. CHC has a high light output of up to 54,000 photons/MeV, and its energy resolution is estimated to be 3.3%, from full width at half maximum (FWHM), at 662 keV. In order to improve the energy resolution, we focused on its non-proportional response. In the case of LaBr_3 , the non-proportional response improved by Sr^{2+} -doping [3]. Therefore non-proportional response and energy resolution for CHC might be improved by doping alkaline earth metals as well. In this study, we report the effect of AE^{2+} -doping (AE^{2+} is alkaline earth metals; Mg^{2+} , Ca^{2+} , Sr^{2+} and Ba^{2+}) into Hf^{4+} site on scintillation properties.

Non-doped and AE^{2+} -doped CHC crystals were synthesized from 99.9%-pure (Zr-free) HfCl_4 , 99.99%-pure CsCl , 99.99%-pure MgCl_2 , 99.99%-pure CaCl_2 , 99.998%-pure SrCl_2 and 99.99%-pure BaCl_2 from a nominal composition of $\text{Cs}_2(\text{Hf}_{0.995}\text{AE}_{0.005})\text{Cl}_6$ by the vertical Bridgman method. Crystal phases were identified by powder X-ray diffraction. Excitation/emission wavelengths were evaluated from photo- and X-ray excited radio-luminescence spectra. Light output, its non-proportionality, energy resolution and scintillation decay constant were evaluated using a ^{137}Cs gamma-ray source.

Finally, we succeeded in growing non-doped and AE^{2+} -doped CHC single crystals. The crystal structure of all specimens was determined as Fm-3m. No other phase was observed. Non-doped CHC showed broad emission around 400 nm under X-ray excitation. The light output and energy resolution were estimated to be 42,000 photons/MeV and 5.2% at 662 keV (FWHM), respectively. The scintillation decay constant was estimated using double exponential fitting, and fast component and slow component were determined to be 0.27 μs (4.5%) and 5.52 μs (95.5%), respectively.

On the other hand, radio-luminescence emission spectrum of $\text{Mg}:\text{CHC}$ was the same as for the non-doped CHC. Its light output and FWHM energy resolution were estimated to be 45,000 photons/MeV and 6.0% at 662 keV, respectively. The scintillation decay constant consisted of fast 0.69 μs (7.5%) and slow 5.99 μs (92.5%) components. In presentation, we show the results of other AE^{2+} -doped CHC and discuss the relationship between their scintillation properties and co-doped elements.

References

- [1] P. Dorenbos, *Nucl. Instrum. Meth. in Phys. Res. A*, **486** (2002) 208
- [2] A. Burger *et al.*, *Appl. Phys. Lett.*, **107** (2015) 143505
- [3] S. Alekhin *et al.*, *J. Appl. Phys.*, **113** (2013) 224904

Has accepted

Primary author: Mr KODAMA, Shohei (Tohoku University)

Co-authors: Dr KUROSAWA, Shunsuke (New Industry Creation Hatchery Center, Tohoku University, Sendai, Japan, Faculty of Science, Yamagata University, Japan); Mr FURUYA, Yuki (Tohoku University); Dr PEJCHAL, Jan (Institute of Physics, AS CR, Prague, Czech Republic); Dr KRAL, Robert (Institute of Physics, AS CR, Prague, Czech Republic); Dr YAMAJI, Akihiro (Institute for Materials Research, Tohoku University, Sendai, Japan); Dr

OHASHI, Yuji (Institute for Materials Research, Tohoku University, Sendai, Japan); Dr KAMADA, Kei (NICHe, Tohoku Univ., C&A Corp.); Dr YOKOTA, Yuui (New Industry Creation Hatchery Center, Tohoku University, Sendai, Japan); Prof. NIKL, Martin (Institute of Physics, AS CR, Prague, Czech Republic); Prof. YOSHIKAWA, Akira (Tohoku University)

Presenter: Mr KODAMA, Shohei (Tohoku University)

Session Classification: Poster Session 3

Track Classification: P5_characterization