



Contribution ID: 53

Type: **not specified**

Review of various fabrication methods: which is more promising for high J_c/HF ? (20+5)

Presenter: TERESA PUIG TBC

Session Classification: .