



Contribution ID: 39

Type: poster

Crystallographic study of new phases from the U–Zn–Al ternary system

Monday, 29 March 2010 11:00 (5 minutes)

Crystallographic study of new phases from the U–Zn–Al ternary system

Yu.V. Verbovitskiy, A.P. Gonçalves

Departamento de Química, Instituto Tecnológico e Nuclear/CFMC–UL, 2863–953 Sacavém, Portugal
yuryvv@bigmir.net

Uranium based intermetallic compounds have been intensively studied due to their unusual ground states and behaviours (as intermediate valence states, heavy fermion behaviours, unconventional superconductivity, etc.). The binary U–Zn system is characterised by the existence of two compounds, $U_{12}Zn_x$ (high-temperature form of $SmZn_{12}$) and U_2Zn_{17} (crystallizing in two polymorphic modifications, with Th_2Zn_{17} and Th_2Ni_{17} structure types, respectively), which show coexistence of magnetism and heavy fermion behaviour [1,2]. Albeit this, the study of U–Zn–X (X = p element) ternary systems is still scarce. This work is a part of our systematic investigation of uranium–d- and p-metal alloy systems and consists on the exploration of the U–Zn–Al phase diagram and identification of the ternary compounds and solubility ranges.

The samples were synthesized at 950°C from the pure elements, inside quartz ampoules under vacuum. No reaction with the quartz ampoules was observed. The obtained products were characterized by using X-ray powder diffraction techniques. Needle-shape high quality crystals were selected from crushed samples with nominal $U_{10}Zn_{60}Al_{30}$ composition and used in the X-ray diffraction measurements. The experiments were made at room temperature by using a four-circle Nonius CAD4 diffractometer with graphite monochromatized $Mo\ K\alpha$ -radiation and a scintillation counter with pulse height discrimination. Scans were taken in the $\omega/2\theta$ mode. Empirical absorption corrections were applied on the basis of Ψ -scan data. The crystal structure was refined using Shelxl-97 [3] (full-matrix least-squares on F2). The unit cell parameters were obtained by least-squares refinement of the 2θ values of 25 intense and well-centered reflections from various parts of the reciprocal space ($16^\circ < 2\theta < 36^\circ$).

The X-ray powder diffraction data of the as-prepared $U_{10}Zn_{60}Al_{30}$ sample shows the presence of three phases: $Zn_{1-x}Al_x$ (Mg-type), binary UAl_3 (AuCu₃-type) and hexagonal phase $U_x(Zn_{1-y}Al_y)_z$, with cell dimensional: $a = 9.047(1)\ \text{Å}$, $c = 8.858(1)\ \text{Å}$, $V = 627.9(1)\ \text{Å}^3$. The cell dimensions fitting, from the 25 reflections and performed for several single crystals, gave always similar results: $a \sim 9.03\ \text{Å}$, $c \sim 8.82\ \text{Å}$, $V \sim 622\ \text{Å}^3$. After testing various models for well-known structures of binary R–Zn and ternary R–Zn–X compounds (R = rare earth), our attention was stopped on the high-temperature form of $SmZn_{12}$ type structure (space group P6/mmm). In a first stage this structure type was adopted in the $U_x(Zn_{1-y}Al_y)_z$ structural refinement from the single crystal X-ray diffraction data and residuals $R_1 = 0.0642$, $R_w = 0.1154$ (405 F2 values, 41 variables) were obtained. The composition of this hexagonal phase was also refined, being obtained $U_{1.12}Zn_{9.51}Al_{1.71}$ (= $U_9Zn_{77}Al_{14}$). However, quite high residual factors still remain, which could indicate that the structure of the above mentioned phase was not exactly of the $SmZn_{12}$ type, but some derived from it. In a second step direct methods were used and the $U_x(Zn_{1-y}Al_y)_z$ crystal structure was determined and refined.

Acknowledgments

This work was partially supported by FCT, Portugal, under the contract No. PTDC/QUI/65369/2006 and No. SFRH/BPD/34840/2007.

References

[1] P. Chiotti and J.T. Mason. J. Less-Common Metals 40 (1975) 39.

[2] H.R. Ott, H. Rudigier, P. Delsing and Z. Fisk. Phys. Rev. Lett. 52 (1984) 1551.

[3] G.M. Sheldrick. SHELX97—A Program Package for the Solution and Refinement of Crystal Structures
Universität Göttingen, Germany, 1997.

Primary author: VERBOVYTSKYI, Yuriy (Instituto Tecnológico e Nuclear)

Presenter: VERBOVYTSKYI, Yuriy (Instituto Tecnológico e Nuclear)

Session Classification: Introductions to Posters

Track Classification: Inorganic, organometallic chemistry