ESIPAP European School of Instrumentation in Particle and Astroparticle Physics

Additve Manufacturing

Thinking about innovation

Feedback on implementation on Additive Manufacturing Technics
For designing and manufacturing of definitive mechanical parts, since 1995
When could I use additive manufacturing ? Where could we find some informations ? Who could help ?



Enigmass

IPHC Institut Pluridisciplinaire Hubert Curien STRASBOURG
http://www.iphc.cnrs.fr/

cnrs IN2P3 Les deux infinis

www.cnrs.fr
IN2P3
http://institut.in2p3.fr/

Additve Manufacturing

Thinking about innovation

IPHC
Institut Pluridisciplinaire Hubert Curien
STRASBOURG
http://www.iphc.cnrs.fr/

Summary

Enigmass

www.cnrs.fr
IN2P3
http://institut.in2p3.fr/

Institut Pluridisciplinaire Hubert Curien STRASBOURG
http://www.iphc.cnrs.fr/

1- two complementary aproaches

specific contexts

1- two complementary approaches



Machining
Metal cutting

Metal chip



Source : http://www.sandvik.coromant.com/

1- two complementary approaches



1- two complementary approaches



1- two complementary approaches



Metal powder and laser…
Direct manufacturing

scanner

engineering

Points cloud

Catia V5 workbenches :
Used workbenches : STL, Part Design, GSD, QSR, DSE

CAD Modeler
CATIA V5

FEM specific files
ANSYS, COMSOL, other

Numerical method

CAD part geometry

STL workbench
CATIA V5

AM specfic file

stl file

Sending to 3D printer

Manufacturing by Additive Manufacturing

1- two complementary approaches : numerical method

Base principle

Additive Manufacturing (AM) is defined by ASTM norm under the name ‘Fast Manufacturing’

‘3D printing’ is the common name to describe all the process which use AM.

Invention of stereolithography begins in 1980’s, in a chemical school in Nancy (France).
Industrialisation begins in 1986 in USA by 3D Systems society.



1- two complementary approaches : numerical method

the revolution …



1- two complementary approaches : numerical method

the revolution …



1- two complementary approaches : numerical method

Main existing printing processes …



-> http://fr.wikipedia.org/wiki/Impression_tridimensionnelle
http://en.wikipedia.org/wiki/3d_printing

1- two complementary approaches : numerical method

Inseparable items…



www.cnrs.fr
IN2P3
http://institut.in2p3.fr/

Institut Pluridisciplinaire Hubert Curien STRASBOURG
http://www.iphc.cnrs.fr/

2- main additive manufacturing technics in use

processes, machine manufacturers, partners, …

2- Manufacturing techniques at the service of the additive manufacturing

Stratoconception (hybrid principle : stack of machined plates or cutted sheets : glued, welded or screwed together)

Stratoconception original patent

Image Source : http://www.freepatentsonline.com/6745446.html



2- Manufacturing techniques at the service of the additive manufacturing

Stratoconception (hybrid principle : stack of machined plates or cutted sheets : glued, welded or screwed together)

mold

model



packaging

Image Source : http://www.freepatentsonline.com/6745446.html

Fused Deposition Modeling at CEMES laboratory (CNRS, Toulouse)

machines DIMENSION and Stratoconcept (manufacturer : STRATASYS)



The CEMES I3D office proposes a pool of shared machines ... http://www.i3d.cemes.fr/

Fused Deposition Modeling

What's coming out of the printer ?



Cleaning by immersion : support material is soluble
! two different materials

IPHC 3D fdm printer
'Makerbot Replicator 2X'

Direct 3D printing or through SD card storage



goal :
good Design and final parts

Maximum printing size :
150x250x150 mm

Layer thickness : 0.1, 0.2 or 0.3 mm

Printing time :
0.5 – 25 hours / peace

Used material : ABS (several colors)

Used with raft and support : ABS

Price : ~3000 € HT
Test review : https://www.3dhubs.com/3d-printers/replicator-2x
Seller : http://www.machines-3d.com/

IPHC 3D fdm printer
‘ZORTRAX M200’

Direct 3D printing or through SD card storage

goal :
good Design and final parts

Maximum printing size :
200x200x180 mm

Layer thickness : 0.09, 0.14 or 0.19 mm

Printing time :
0.5 – 72 hours / peace

Used material : ABS (several colors)

Used with raft and support : ABS

Price : ~2000 € HT
Test review : http://www.lesnumeriques.com/imprimante-3d/zortrax-m200-p22789/test.html
Seller : http://www.machines-3d.com/

Photopolymer with UV curing with CADINDUS Society (Mulhouse, F) and pôle ORTECH from LpoDeck (Guebwiller, F)





EDEN machine
by OBJET Society

Photos INTERNET (Société OBJET)

Bimaterial production
(with CONNEX 500)

Unremovable parts : bearing

spring



Photopolymer UV curing



Cleaning : water jet and scraper
! resin support and part : same chemical base

3D printing with EDEN 330, viewed by electron microscope ESEM (IPHC)







Sample fabrication
10mm x 10mm x 1mm

Layers thickness : 16µm











©IPHC / DEPE / ESEM : Environnemental Scanning Electron Microscope
Source : http://en.wikipedia.org/wiki/Environmental_scanning_electron_microscope

Selective laser sintering (sls)

PA parts production at LpoDECK and 3DPROD (France)

Ofen temperature : 170°C + laser
Layer thicknesss : ~100 µm



Image source : http://3dprinting.com/

EOS sample



Ensemble indémontable
Couches d'épaisseur 0.1mm

EOS Formiga P100 : Polyamid (PA) printing

metal or ceramic possible on other machine

3D printing with EOS FORMIGA 100, viewed under ESEM (IPHC)

Powder grain size less than 100 µm

Partially melted on surface





©IPHC / DEPE / ESEM : Environnemental Scanning Electron Microscope

Scale effects

alumide





zcorp

argent





eos

sculpteo Source : http://www.sculpteo.com/fr/help/

Stereolithography (SLA)

Photo-solidification : 3D printing patent (1986)
Using of a vat of liquid ultraviolet curable photopolymer and ultraviolet laser



Source : http://en.wikipedia.org/wiki/Stereolithography

Direct Metal Laser Sintering (DMLS)

Today, the way to produce metal parts…



Laser : ~200 W
Layer thicknesss : ~20 µm

Image source : http://www.custompartnet.com/wu/direct-metal-laser-sintering/

Laser cladding (CLAD)





Laser and powder stream are coaxial

Source : http://en.wikipedia.org/wiki/Cladding_(metalworking)

DMG MORI
LASERTEC 65 AM
special manufacturing machine





- **Laser CLADDING**
- **Machining**
- **Repairing**
- **Coating**

Source : http://www.dmgmori.com/webspecial/journal_2014_1/en/lasertec-65.htm

2- Main 3D additive manufacturing technics in use

1- **fdm process** (fused deposition molding) : thermoplastic fused deposition / extruder hole diameter ~ 0,4 mm

2- **Objets 3D printers** (Objet.com ; polyjet printing) : thin layers (less than 30 µm)
Remove with spatule, remove support material with water jet
Clear the tray with spray / Build tray is ready for the next model

3- **voxeljet** (voxeljet.com)
Pouder and binder jet
Parts complete curing after 24 h standing
Make vax parts for lost wax casting
Layer thickness 0,006 inch
Depoudering station to remove the pouder by hand to prevent damage
Final curing process : low temperature for 5 h
When curing is complete, remaining excess pouder is removed with low pressure air jet
Final step : quick dip in vax to seal the part
A heater can as used to remove the excess vax from the surface

4- **stratoconception**
Cutting parts in thin hard or soft plates (foam, wood, plastic, metal, …)
Stack the pieces to construct the whole geometry

5- **stereolithography** (materialise.com ; SLA = StereoLytography Apparatus)
Pieces are produced in liquid polymer, with a same material builded supporting structure.
The polymer is solidified layer by layer : during the process, the pieces supporting tray go down in the polymer.

6- **polyshape process** (SLS = Selective Laser Sintering ; DMLS = Direct Metal Laser Sintering, SLM = selective laser melting)
Pouder layers with selective laser melting or sintering, layer by layer (plastic or metal)
The support, the pouder and the pieces are cooled before cleaning

7- **CLADDING :**
Simultaneous metal powder projection and melting by laser : the melted powder solidifies and forms the part layer by layer. The support can be curved.

Sources : http://www.industrie-techno.com/sept-facons-de-fabriquer-en-3d.23174
http://en.wikipedia.org/wiki/Cladding_(metalworking)

2- Main direct fabrication technics in use

Several machine manufacturers …



source : http://reprap.org/

2- Main direct fabrication technics in use – Who could make the part ?



www.cnrs.fr
IN2P3
http://institut.in2p3.fr/

Institut Pluridisciplinaire Hubert Curien STRASBOURG
http://www.iphc.cnrs.fr/

3- achievement examples

geometrical optimization in an IPHC project,
Quick overview of
some research and development examples in several domains

Example of numerical method at IPHC



Imaging System

AMISSA

developped and used at IPHC

Rat or mouse



3D images superposition
Acquisition by µTEMP and µCT
(skeleton, flesh
and localisation of cancer in mouse)



Cloud of points

Example of numerical method at IPHC





3D CAD volume
After treatment with CATIA V5
(skull and head of a rat)



.stl printing file



Not well cleaned part

Impression 3D

Rat skull printing

Example of numerical method at IPHC

- Mouse supporting during scanning time

Machined solution







Shell FEM Model

CATIA V5

Bed first generation
End-peace ϕ 30 mm





Rapid prototyping
Photopolymer

18 cm (thick. 0.4mm)



Technics Association

Requests :
-General Anesthesia
-Mechanical supporting of mouse (40 gr)
-Material optimization around the mouse
-Possibility of hot air circulation

Produced by CADindus Ingénierie et services CAO DAO

FDM by STRATASYS/DIMENSION (at CEMES Toulous)

ABS thread / layer thickness = 0,254 mm

Extruder nozzle diameter 0,4 mm



1 wire wall thickness



2 wire wall thickness





Photopolymer support by OBJET 250

Material evolution, in water immersed part and leave in sun shine



Thickness wall = 0,4 mm

Unused part



Two identical parts

Totally removed supporting resin
Total in water immersion
Solar UV ray exposition

After 3 days :
- Deformation
- Hardening
- Cracks

Produced by CADindus Ingénierie et services CAO DAO

Example of numerical method at IPHC

- Rat supporting during scanning time



optimization



End-peace ϕ 40 mm



CATIA V5

PA SLS



Produced by

3DProd
Du Concept à la Réalité

Requests :
-General Anesthesia
-Mechanical supporting of rat (800 gr)
-Material optimization around the mouse
-Possibility of hot air circulation

CADVISION / IPHC manufacturing test
Mesurements on fdm produced part
on Fortus 250 Stratasys machine, with layer thickeness of 0,178 mm

IPHC contact IPHC : Christophe Ruescas, christophe.ruescas@iphc.cnrs.fr / Marc Krauth, marc.krauth@iphc.cnrs.fr





Some theoretical values



Hole ø 5 mm

ABS fdm part



Assembled parts

Height 73 mm
Thickness plate 12 mm
Cylindrical part thickness 4 mm



Differencies between several numerical dimensions and real produced dimensions are between 0,04 and 0,2 mm .

Part produced by Cadvision
Contact : Stefka BARZAKOVA / stefka@cadvision.fr

Photos : ©IPHC.cnrs.fr

Décembre 2013

Print Troubleshooting

Several possible origins :

- due to a technical problem with the printer

- due to a bad designed part geometry





Warping
Delamination
Internal constraints

Source : http://reprap.org/wiki/Print_Troubleshooting_Pictorial_Guide

Source : http://www.industrie-techno.com/fleurs-de-techno.27541

Techno flower

Printed by OBJET connex

multimaterial 3D printing

Inflatable structure





Source : http://www.contourcrafting.org/

Building 3D printing – concrete masonry unit -1-

Contourcrafting.org



Extrusion of
high performance concrete
Strength : 3 000 to 10 000 psi

NASA developpement

Source : https://www.youtube.com/watch?v=ehnzfGP6sq4&list=PLwZuNacIKo6a3C1tavZ5hnS2WABYSGbJv
http://www.contourcrafting.org/

Building 3D printing – concrete masonry unit -2-



Source : https://www.youtube.com/watch?v=EfbhdZKPHro&list=PLwZuNacIKo6a3C1tavZ5hnS2WABYSGbJv

Source : http://www.dvice.com/2013-5-22/mataerial-anti-gravity-3d-printer

Robot 3D printing



Architecture models

How it was…
How it could be…



Source : http://www.midwestmodel.com/pagesroot/pages/ProjectDetails.aspx?ProjectId=339&DetailsType=ATOZ



Source : http://www.hp3dprinting.co.uk/applications.htm

Automobile Design

research and development department
Combination of manufacturing technics



First Asian 3D Print Fa3D printing is also present in the field of fashionshion Show

2013
First fashion meeting with 3D printed wears, organized by Materialise, belgian company.

Source : http://www.numerama.com/magazine/26298-un-defile-de-mode-pour-l-impression-3d.html

“The clothing was modeled as it would be if it were knitted with thread inside the 3D software,” Ono told 3DPrint.com.

Source : https://3dprint.com/149870/3d-printed-amimono-woven-fashion/

Nike Debuts First 3D-Printed Football Cleat



Source : http://mashable.com/2013/02/27/nike-3d-printed-cleat/

MADE IN 3D challenge - 2011

This strange parts supports an Iphone and emplifys sound coming out the phone.

To make a 3D ready printing design is the main goal.

This part is called the ‘Mush’ and was designed with CATIA V5 by a young designer .

Source : http://blogs.cotemaison.fr/archiboom/2011/06/26/made-in-3d-%E2%80%93-design-et-impression-3d/
http://www.3dvia.com/blog/made-in-3d-challenge/

3D Printing Pen (Sculptures drawing)
February 19, 2013



Source : http://www.thisiscolossal.com/2013/02/the-worlds-first-3d-printing-pen-that-lets-you-draw-sculptures-in-real-time/

A kid drawing converted into 3D part

a sheet of paper becomes a 3D object

Source : http://journalmetro.com/dossiers/la-liste-du-lundi/338524/objets-3d/

Edible prints

Source : http://blsciblogs.baruch.cuny.edu/yomara89/?p=7

Candy prints

Source : https://3dprinting.com/food/

FabRx Produces Customised Medicine Tablets Using Sintratec SLS Printer

Source : https://www.sciencedirect.com/science/article/pii/S0378517317305902

Research in 3D Printing of Food for People with Swallowing Difficulties













Source : https://www.knepublishing.com/index.php/KnE-Engineering/article/view/591/1865

Food printing

Food Ink enterprise



Chocolate 3D printing

Source : http://www.lesimprimantes3d.fr/limprimante-3d-fabrique-chocolat/

http://www.materiel.net/minisites/guide-achat-imprimante-3d/les-applications-3d-futures.php

Meat 3D printing



Source : http://veganvine.blogspot.fr/2013/08/you-can-take-meat-out-of-animal-but-you.html

Source : http://veganvine.blogspot.fr/

Source : http://www.peta.org/issues/animals-used-for-food/meat-wastes-natural-resources/

Industry news

Renault Trucks enterprise prints their motors

1/2017

Source : https://www.industrie-techno.com/renault-trucks-imprime-ses-moteurs-en-3d-metal.47535

Michelin and Fives enterprises wants to be leaders in metal additive manufacturing

9/2015

Source : https://www.industrie-techno.com/impression-3d-metal-michelin-et-fives-se-positionnent-sur-le-marche.39690

BeAM entrerprise adds its technology in Fives 5 axis production machines

1/2015

Source : https://www.industrie-techno.com/fabrication-additive-beam-integre-sa-technologie-aux-batis-5-axes-de-fives.38970

-> CLAD printing process (IREPA Laser)
See machines by DMG MORI

-> http://www.beam-machines.fr/

Source : http://www.youtube.com/watch?v=l0SXlkrmzyw

Leap Fuel Nozzle







Aviation développement :
Problem of nozzle : cooking with carbon deposition
Function : Spray fuel into combuster

- The temperature increases up to 3000°C -

Solution with DMLS :
Efficiency
engine durability (X5)
18 parts in one single piece
Weight -25%
Better than casting, machining, welding,…
Production speed x20

Numerical method

CAD – DMLS – PLASTIC INJECTION

Source : http://machinedesign.com/3d-printing/difference-between-machined-and-3d-printed-metal-injection-molds







Industry news

Printing maraging steel parts

Source : http://www.incept3d.com/metal--dmls.html

Printing Titanium bike frame

Source : http://inhabitat.com/empire-cycles-unveils-the-worlds-first-ultralight-3d-printed-titanium-bike/



Printing completed wirh machining

Source : http://www.3ders.org/articles/20120918-shell-makes-complex-structures-with-3d-printing.html

Printing Nylon bike

Source : http://inhabitat.com/3d-printed-air-bike-is-as-strong-as-steel-but-13rd-the-weight-of-aluminium/

Implants



Custom Prosthetics



Source : http://www.treehugger.com/green-architecture/heavy-metal-meets-downloadable-designs-3d-printing-from-cad-to-metal.html
http://www.materiel.net/minisites/guide-achat-imprimante-3d/les-applications-3d-futures.php

ESA : 3D Printing Metals on earth and in Space

The AMAZE project team printed its logo in titanium as an intricate net shaped to millimeter-level precision to demonstrate what metal 3D printing can do. The project is working with materials that can withstand temperatures up to 3500 °C and involves 28 industrial and educational partners across Europe.
(Source: ESA-N. Vicente)



Titanium 3D printing



Source 2013 : http://www.esa.int/Our_Activities/Human_Spaceflight/Research/3D_printing_for_space_the_additive_revolution

NASA : 3D Printing Metals on earth and in Space





NASA-funded research by University of Southern California professors Behrokh Khoshnevis, Madhu Thangavelu, Neil Leach, and Anders Carlson is exploring how structures on the moon can made using the Contour Crafting robot. Under NASA's Innovative Advanced Concepts program, the researchers aim to develop methods for creating infrastructure, such as roads and landing pads, to support human settlement on the moon. The technology can create structures *in situ* from local materials, which is especially important for long-term, continuously expanding operations on the moon. For example, the team is exploring a nozzle system that heats lunar soil into a cement-like paste. In this visualization by Behnaz Farahi and Connor Wingfield, a lander descends on a pad fabricated by the Contour Crafting robot.
(Source: University of Southern California/Contour Crafting)

www.cnrs.fr
IN2P3
http://institut.in2p3.fr/

Institut Pluridisciplinaire Hubert Curien STRASBOURG
http://www.iphc.cnrs.fr/

4- some 3D printers

ESIPAP European School of Instrumentation in Particle and Astroparticle Physics

4- some 3D printers

Stratasys uPrint SE

ABSPlus thermoplastic thread
With soluble resin support
Oven temperature : 260°C
Layers thickness between 0,12 and 0,25 mm
Geometrical precision ~0,2 mm
Production 3D array 152 x 203 x 152 mm
~20 k€

Source : http://www.u-print.fr/

4- some 3D printers

UP MINI 3D PRINTER
ABS withe thread
layers 0,15 to 0,40 mm
3D array : 140 x 140 x 135 mm
~3k€





Source : http://modeler3d.fr/

3ntr
INDUSTRIAL GRADE 3D PRINTERS

A2 V2

3 nozzles
ABS, PLA, NylonCarbon, PC, PC-ABS, PETG, …
thermoplastic thread
With soluble resin support (SSU01)
Regulated oven temperature : 80 °C
Max nozzle temperature : 410 °C
Max plate temperature : 135 °C
Minimum layer thickness : 0,05 mm
Resolution : 0,015 mm
Geometrical precision ~0,2 mm
Production 3D array 620 x 350 x 490 mm
~25 k€

Source : http://www.3ntr.eu/a2/

IPHC
Institut Pluridisciplinaire Hubert CURIEN
STRASBOURG

Apium Additive Technologies GmbH

Apium P 155

High performance polymers
PEEK, POM-C, PVDF, PEI Ultem 1000 …
thermoplastic thread
Specific regulated oven temperature
Max nozzle temperature : 520 °C
Plate temperature : up to 120 °C
Minimum layer thickness : 0,1 mm
Machine resolution : X Y 0,0125 mm / Z 0,05 mm
Product resolution : X Y 0,5 mm / Z 0,1 mm
Production 3D array 145 x 135 x 148 mm
~35 k€

Source : http://apiumtec.com/

PEEK

KREOS

3D Roboze One+400

High performance polymers
PEEK, Carbon Pa, PC, PMMA, …
thermoplastic thread
Specific regulated oven temperature
Max nozzle temperature : 520 °C
Plate temperature : up to 150 °C
Minimum layer thickness : 0,1 mm
Machine resolution : 0,05 mm
Production 3D array 200 x 200 x 200 mm
~40 k€

Source : http://www.primante3d.com/kreos-roboze-20160520/

Objet30 Pro

Polyjet printer
3D array : 294 x 192 x 148.6 mm
Layers thickness 28 microns
Layers thickness 16 microns with VeroClear material
Resolution: 600 x 600 x 900 dpi
Precision about 0.1 mm
7 different photopolymers (indépendant prinitings)
With resin support material
~20k€

Source : http://fr.objet.com/

EDEN 260 at Pôle ORTECH (Lycée Théodore Deck, in Guebwiller, France)

http://www.lyceedeck.fr/poleortech/equip_eden.html

4- some 3D printers

FORMIGA P100
sls PA 100µm
~200 k€
Maintenance ~2-4k€/an

FORMIGA P100 at Pôle ORTECH (Lycée Théodore Deck, in Guebwiller, France)

http://www.lyceedeck.fr/poleortech/equip_eos.html

Source : http://www.eos.info/en

Powder and binder jet
By Zcorp (3D System since 2012)

ZPRINTER 150 by ZCORP
monochrom (white)
Resolution : 300 x 450 dpi
minimal size : 0,4 mm
vertcal creation speed : 20 mm/heure
fabrication maximal size : 236 x 185 x 127 mm
layer thickness 0,1 mm

Zprinter 150
Monochrom voxeljet ~15k€

Zprinter 250
Polychrom voxeljet ~25k€



Source : http://www.zcorp.com/
(this adress doesn't work anymore)

Powder and binder jet
By VOXELJET

Powder = PMMA or SAND
Print resolution x, y 600 dpi
Layer thickness 120/300 µm
Build speed 15,4 mm/h (=123 l/h)

build space : **4000 x 2000 x 1000 millimetres**

voxeljet

Source : http://www.voxeljet.de/en/systems/vx4000/

3Z MAX printer by SolidScape

Precision and High quality wax printing

For lost wax casting

Source : http://www.multistation.com/3Z-MAX

FOODINI by Natural Machines : 3D food printer, printing and cooking at the same time







FOODINI SAVORY SWEET FRESH

A 3D FOOD PRINTER

A new generation kitchen appliance that combines technology, food, art and design.

Source : https://www.naturalmachines.com/

www.cnrs.fr
IN2P3
http://institut.in2p3.fr/

Institut Pluridisciplinaire Hubert Curien STRASBOURG
http://www.iphc.cnrs.fr/

5- Materials

Several possible materials used in 3D printing industry

Several plastic materials by STRATASYS

Stratasys fdm production possibilities :

ABSplus-P430, ABSi, ABS-E SD7, ABS-M30, ABS-M30i, PC-ABS, PC-ISO, PC, Nylon 12, ULTEM-9085, PPSF PPSU

Source : http://www.stratasys.com/materials/fdm/compare-fdm-materials

Stratasys Polyjet plastic production possibilities :

Vero, Translucent Rigid, High Temp, Durus, Digital ABS, Digital ABS2, Tango (Rubber-Like / Flexible), Performance Digital, Rubber-Like Digital, Biocompatible

Material Mimic : Polypropylene – PP, High-Density Polypropylene – HDPE (PEHD), Polystyren – PS, Poly Methyl Methacrylate – PMMA (plexiglas), Polycarbonates – PC, Acrylonitrile Butadiene Styrene – ABS, High-Impact Polystyrene – HIPS, Styrene-Based Thermoplastic Elastomers, Ethylene Propylene Diene Monomer M-class – EPDM Rubber,

Source : http://www.stratasys.com/materials/polyjet/compare-polyjet-materials

http://www.stratasys.com/

Several plastic and metal materials by EOS

EOS SLS plastic production possibilities :

Alumide (polyamide alumium filled), CarbonMide (polyamide carbon fiber-reinforced), PEEK HP3 (PEEK, polyaryletherketone), PA 1101 (PA11), PA 2015 (PA12), PA 2200, PA 3200, PrimeCAST 101 (PS, polystyrene),

Source : data sheet on http://eos.materialdatacenter.com/eo/standard/main/ds

EOS DMLS metal production possibilities :

Aluminium AlSi10Mg, CobaltChrome MP1, CobaltChrome SP2, MaragingSteel MS1, NickelAlloy IN625, NickelAlloy IN718, StainlessSteel GP1, StainlessSteel PH1, Titanium Ti64

Source : http://www.moulds.asia/whats-new/dmls-direct-metal-laser-sintering/

Source : http://www.eos.info/

Several materials by 3D SYTEMS

3D Systems SLA plastic production possibilities : Accura series

Accura 25, 55, 60, 48HTR, ABS Black (SL 7820), ABS white (SL 7810), Amethyst, Bluestone, Casto, Casto Free (SL 7800), CeraMAX Composite, ClearVue, ClearVue Free, e-Stone, Peak, Sapphire, SL 7840, Xtreme, Xtreme White 200

3D Systems SLS plastic production possibilities : CastForm PS and Duraform series
Duraform EX Black, EX Natural, Flex, FR100, GF, HST Composite, PA, ProX

Source : data sheet on
http://www.3dsystems.com/materials/production

3D Printer plastic production possibilities : VisiJet series (27 different materials)

Source :
http://www.3dsystems.com/materials/professional

DMS metal production possibilities :

17-7 PH, Aluminium, Berylium Copper, Brass, Carbon Steel, Copper, Nickel Alloys, Phosphor Bronze, Spring Steel, Stainless Steel, Titanium
Also some finishes : anodized, Heat Treated, Laser Welded, Painted, Powder Coated, …

Source : http://www.3dsystems.com/quickparts/production/quick-sheet-metal

Source : http://www.3dsystems.com/

Material today in use or development in progress

Plastics or 'plastic like'

ABS Acrylonitrile Butadiene Styrene
Nylon
PEHD
Polycarbonate
ULTEM (Stratasys)
PLA
Polyjet Resin
PMMA
PA
PEEK
PSU
Multicolor or not
…

Soluble

PVA
HIPS

Other

Ceramic (ZrO_2, TiO_2, SiC)
Sand
Wax
Alumid

Metals

Aluminium
Nickel
Tantale
Tungsten
Titanium (Ti-6A-4V)
Maraging steel
Stainless steel 316L
Inconel
Cr-Co alloy
Aluminium alloy
Gold, silver

Alternative :

Biological material : bone, lever, skin, …
Meat,
Pizza,
Chocolate, sugar

www.cnrs.fr
IN2P3
http://institut.in2p3.fr/

Institut Pluridisciplinaire Hubert Curien STRASBOURG
http://www.iphc.cnrs.fr/

6- Outlook

ESIPAP European School of Instrumentation in Particle and Astroparticle Physics



Fig. 3



Fig. 4



Fig. 5

Fdm patent is expired in 2009 (fused deposition modeling)

Key 3D printing patent is expired in 2014 (sintering powder by laser)

Apparatus for producing parts by selective sintering
US 5597589 A
Abstract :
An apparatus for selectively sintering a layer of powder to produce a part made from a plurality of sintered layers. The apparatus includes a computer controlling a laser to direct the laser energy onto the powder to produce a sintered mass. The computer either determines or is programmed with the boundaries of the desired cross-sectional regions of the part. For each cross-section, the aim of the laser beam is scanned over a layer of powder and the beam is switched on to sinter only the powder within the boundaries of the cross-section. Powder is applied and successive layers sintered until a completed part is formed. Preferably, the powder dispensing mechanism includes a drum which is moved horizontally across the target area and counter-rotated to smooth and distribute the powder in an even layer across the target area. A downdraft system provides controlled temperature air flow through the target area to moderate powder temperature during sintering.

3D printing has exploded
More possible materials !

5- Outlook



Source : http://www.3ders.org/articles/20130529-mckinsey-report-12-disruptive-technologies-by-2025-3d-printing-included.html

Possibilities for innovation in physics developpements



Including 3D wire screen (filter),
Cooling channels,
Volume optimisation

Without assembling
or
Assembling by glueing, bolting, screwing, …

Multifunctionnal parts

Where are the limits ?

Geometries

Additive Manufacturing Machine

New materials

Plastics,
Metals,
Composites





integration
In existing manufacturing process

EBM
Electron
Beam
Melting

DMLS
Direct
Metal
Laser
Sintering

Some benchmarks :
- Service society : Specialized in additive manufacturing
- Possible plastics : ABS, PLA, PC, PA, Plastique ceramic charged, fibres or aluminium alloy charged,…
- Possible metals : 316L, Ti64, TA6V, maraging steel, CR-CO, Bronze, Inconel, Nickel alloy, aluminium alloy, ceramics, …

Metal 3D Printing Services

I3DFG enterprise



Aluminium, titatium, stainless steel,
maraging steel, inconel (IN718) or customer powder

Source : http://www.i3dmfg.com/industries/tooling/

Aluminum, Stainless Steal, and Titanium DMLS printing possibilities
Source : http://3dprintingcolorado.com/3d-metal-printing/

Post treatment processes



Source : http://www.engineering.com/3DPrinting/3DPrintingArticles/ArticleID/4042/First-Surface-Oberflachentechnik-GmbH-EOS-and-BESTinCLASS-Found-Joint-Venture-for-the-German-speaking-Market.aspx

Smit Röntgen enterprise



Tungsten alloy parts

Source : http://www.smitroentgen.com/

5- Outlook

Be carefull about copyright !

Where is the limit of 3D printing ?

A lot of leaders : each in his domain …

5- Outlook : questions…

When will I use 3D printing technology ?

What have I to do with it ? What can I do with it ?

Just think, simulate and print …

Source : http://www.dezeen.com/2013/02/13/protohouse-2-3d-printed-house-by-softkill-design/

5- Outlook : questions…

How will you use 3D printing ?



Source : http://www.pwc.com/us/en/technology-forecast/2014/3d-printing/features/future-3d-printing.html

Innovation : ears and guns produced by 3D printing
Some steps were forgotten …

And printing something between ears ?

Source : http://www.clubic.com/diaporama/photo-la-semaine-de-flock-enleve-les-bigoudis-de-l-actu-61890/

5- Outlook : questions…

Easy copy

We should be carefull
About file protection



Source : http://textually.org/3DPrinting/2012/12/031489.htm

Futur is 3D printing



Source : http://www.3dprinter.net/3d-printing-the-business-opportunities

www.cnrs.fr
IN2P3
http://institut.in2p3.fr/

Institut Pluridisciplinaire Hubert Curien STRASBOURG
http://www.iphc.cnrs.fr/

Annex

Plastic printing services



Source : http://www.aniwaa.com/blog/the-best-3d-printing-services/

News on Internet



Source : https://fr.pinterest.com/explore/direct-metal-laser-sintering/

Association Française de Prototypage Rapide :
http://www.afpr.asso.fr/

Assises Européennes de Prototypage Rapide :
http://code80.net/afpr/aepr/



National Additive Manufacturing Innovation Institute :

SOURCE : http:/namii.org/resources/presentations/

NATIONAL NAMII ADDITIVE MANUFACTURING INNOVATION INSTITUTE

Hub AM Equipment Entrusted To Date

Equipment	Manufacturer	Model
Fused Deposition Modeling	Stratasys	Fortus 400MC
Selective Laser Melting	Renishaw	AM 250
Bonded Plaster	Z-Corp	Z-Printer 310
Selective Laser Sintering	3D Systems	SLS sPro 60
Wax Depositon	3D Systems	Thermojet
Bonded Refractory Material	ExOne	M-Lab
Material Extrusion (3D Printer)	3D Systems	Cube
Direct Metal Deposition	POM	Synergy 5
Material Extrusion (3D Printer)	3DCAD Printer	Hyrel
Plunge / "Dry" EDM	Sodick (w/ POM Upgrades)	AQ55L

Ancillary/support equipment: CNC milling machine, ovens, chillers, etc.

Distribution A: Cleared for Public Release # 88ABW-2012-5792

77 members from 15 countries

Direct Metal Laser Sintering
About powder production…

Source : http://www.epma.com/

Some Fab Labs in Europe



Source : http://www.fabfoundation.org/

The Fab Charter

What is a fab lab?

Fab labs are a global network of local labs, enabling invention by providing access to tools for digital fabrication

What's in a fab lab?

Fab labs share an evolving inventory of core capabilities to make (almost) anything, allowing people and projects to be shared

What does the fab lab network provide?

Operational, educational, technical, financial, and logistical assistance beyond what's available within one lab

Who can use a fab lab?

Fab labs are available as a community resource, offering open access for individuals as well as scheduled access for programs

What are your responsibilities?

safety: not hurting people or machines
operations: assisting with cleaning, maintaining, and improving the lab
knowledge: contributing to documentation and instruction

Who owns fab lab inventions?

Designs and processes developed in fab labs can be protected and sold however an inventor chooses, but should remain available for individuals to use and learn from

How can businesses use a fab lab?

Commercial activities can be prototyped and incubated in a fab lab, but they must not conflict with other uses, they should grow beyond rather than within the lab, and they are expected to benefit the inventors, labs, and networks that contribute to their success

draft: October 20, 2012

Source : http://www.fabfoundation.org/fab-labs/the-fab-charter/

FABLABs around the world

A Fab Lab in Strasbourg…



3D printer prices

Source : Industrie et Technologies – May 2010

Marque	Multi station	Solido	3D Systems		Zcorporation		Stratasys		Solid scape	Objet
Nom	Extru 3D plastique	SD3000 Pro	V-Flash	Projet 3000 Dentaire	Zprinter 350	Zprinter 650	uPrint	Dimensio n	3D cire	Alaris 30
Taille Objet	60 x 60 x 80 x cm	46 x 77 x 42 cm	66 x 69 x 79 cm	73 x 125 x 150 cm	20 x 25 x 20 cm	25 x 38 x 20 cm	63 x 66 x 78 cm	NC	55 x 49 x 40 cm	82 x 62 x 59 cm
Résolution	400 µm	100 µm	220 µm	328 x 606 dpi	450 x 300 dpi	600 x 540 dpi	200 µm	100 µm	76 µm	600 x 900 dpi
Consomm able	ABS	PVC	FTI230	Bimatériau Support/ré sine	Poudre + liant	Poudre + liant	Bobine ABS	Cartouche ABS	Cire spécifique	VeroWhite
Principe	Extrusion fil plastique	Plastic sheet lamination	Type stéréolitho graphie	Ajout de couches	Jet d'encre couleur sur poudre	Jet d'encre couleur sur poudre	Fused Deposition Modeling	Fused Deposition Modeling	Dépôt de couches cire	Dépôt résine photopoly mère
Prix	1 000 €	7 950 €	9 900 €	70 000 €	22 000 €	50 000 €	11 999 €	15 300 €	31 900 €	34 500 €
Les plus	La moins chère	Faible coût impressio n	Prix peu élevé et simplicité	Wax up dentaire en continue	Proto couleur, faible coût impression (0.1 €/cm³)	Idem Z350 avec bac impressio n plus grand	Technolog ie nid d'abeille, moins de matériau	idem	Haute précision	Qualité impressio n 28 µm
Les moins		Pas de détails très fins			Opacité des pièces	Opacité des pièces	Plateau impressio n petit	Que de l'ABS		

Comparatif Imprimantes 3D du marché - Source : Industrie et Technologies - Mai 2010

SOURCE : http://p1.storage.canalblog.com/16/54/447324/54635666.png

http://souspression.canalblog.com/archives/2010/06/28/18432637.html

www.cnrs.fr
IN2P3
http://institut.in2p3.fr/

Institut Pluridisciplinaire Hubert Curien STRASBOURG
http://www.iphc.cnrs.fr/

6- Workshop

ESIPAP European School of Instrumentation in Particle and Astroparticle Physics

Workshop



Metal powder and laser…
Direct manufacturing



less material waste
create products that is impossible to make with existing machining techniques.

Workshop

1- CAD (presentation)
2- Topological optimisation
3- stl file slicing





less material waste
create products that is impossible to make with existing machining techniques.

Workshop

1- CAD (presentation)

2- Topological optimisation

3- stl file slicing

CATIA V5

Workshop

1- CAD (presentation)

2- Topological optimisation

3- stl file slicing



Plastic
Stork model

CAD logo

CATIA V5

scanned
Stork model
with logger

Numerical method from cloud to simulation

DSE

Cloud of points
in **CATIA V5 environment**…

collaboration UdS LpoDECK IPHC CNRS

QSR

Part Design

Importation
Filtration
Reparation

Automatic
Surface construction

solid

Analysis
and Simulation

Exportation
Simulation


CATIA
© Dassault Systèmes
CATIA ® is a registered trademark of Dassault Systèmes

CATIA V5


esipap
esipap


CATIA V5 - [logo_ESIPAP1.CATPart]
Démarrer SmarTeam Fichier Edition Affichage Insertion Outils Fenêtre Aide
Part1
Plan xy
Plan yz
Plan zx
Systèmes d'axes
Relations
Corps principal
esipap
Analyse
Sélectionnez un objet ou une commande


CATIA V5 - [lego_ESIPAP1.CATPart]
Démarrer SmarTeam Fichier Edition Affichage Insertion Outils Fenêtre Aide
Part1
Plan xy
Plan yz
Plan zx
Systèmes d'axes
Relations
Corps principal
Esquisse.7
Extrusion.2
Esquisse.5
Assemblage.1
Corps de pièce.2
Poche.2
Esquisse.11

Workshop

1- CAD (presentation)

2- Topological optimisation

3- stl file slicing

ON YOUR DESKTOP

Where should be the marerial to optimise the piece response ?

INSPIRE

solidThinking / WHERE IDEAS TAKE SHAPE

http://www.altairhyperworks.com/product/solidThinking-Inspire

SolidThinking/University Products :

http://www.solidthinking.com/DownloadProducts.aspx?category=Download&item=Products

Altair contact :

Julien Grezolle, Application Engineer, jgrezolle@altair.com

Altair HyperWorks

Altair HyperWorks: Simulation-driven Innovation



HyperWorks is the most comprehensive open-architecture simulation platform, offering technologies to design and optimize high performance, efficient and innovative products.

Drive Innovation

Simulate Everything

Interoperate Freely

Access it All

Freed HyperWorks Student Licenses, Training & Online Certification …

Source : https://www.bing.com/videos/search?q=altair+inspire+use+youtube&view=detail&mid=838D71F1F3945CA2FF19838D71F1F3945CA2FF19&FORM=VIRE


File
Edit
View
Geometry
Structure
Files
Measure
Move
Home
Points/Lines
Rectangles
Circles
Arcs
Trim/Break
Patch
PolyNURBS
Create
Push/Pull
Mirror
Scale
Boolean
Cut
Simplify
Midsurface
Modify
Push/Pull faces (p)
Revolve Face
Mirror Parts
Scale Parts
Combine
Substract
Intersect
Chose target
Cut by plane
Remove
Imprints/Rounds/Holes/Plug
Middle between faces
Automatic search
PolyNURBS
Push/Pull
Mirror
Scale
Boolean
Modify
Create
Wrap
+/-
Loop
Bridge
Sharpen
Scale
Boolean
Modify
Cut
Combine
Subtract
Intersect
Combine
Push/Pull
Mirror
Scale
Boolean
Modify
Cut
Simplify
Midsurface
Imprints
Rounds
Holes
Plug
Find
Remove


File
Edit
View
Geometry
Structure
Files
Measure
Move
Home
Fasteners
Joints
Contacts
Connections
Loads
Disps
Accels
Temps
Materials
Masses
Shape Controls
Setup
Analyze
Optimize
Run
Apply Force/Torque/Pressure
Apply Support
Apply Displacement Constraints
Apply Enforced Displacements
Apply g-loads
Apply Angular Velocity and Acceleration
Apply Temperature
Apply Material
Add/Edit Concentrated Mass
Support and Location
Move : Align Tool with Global Axis
Align Tool with support
Add/Edit Symmetric Control
Draw Directions
Parts and Materials
Parts
Material Library
My Materials
Material
E
Nu
Density
Yield Stress
Coefficient of Thermal Expansion
Steel (AISI 304) 195.000E+09 Pa 0.290 8.000E+03 kg/m3 215.000E+06 Pa 17.300E-06 /K
Steel (AISI 316) 195.000E+09 Pa 0.290 8.000E+03 kg/m3 205.000E+06 Pa 16.000E-06 /K
Steel (AISI 1015) 200.000E+09 Pa 0.290 7.870E+03 kg/m3 285.000E+06 Pa 11.900E-06 /K
Steel (AISI 1040) 200.000E+09 Pa 0.290 7.850E+03 kg/m3 350.000E+06 Pa 11.300E-06 /K
Steel (AISI 1080) 200.000E+09 Pa 0.290 7.870E+03 kg/m3 380.000E+06 Pa 14.700E-06 /K
Steel (AISI 4130) 200.000E+09 Pa 0.290 7.870E+03 kg/m3 360.000E+06 Pa 13.700E-06 /K
Steel (AISI 4142) 200.000E+09 Pa 0.290 7.870E+03 kg/m3 585.000E+06 Pa 12.200E-06 /K
Aluminum (2024) 75.000E+09 Pa 0.330 2.770E+03 kg/m3 75.000E+06 Pa 22.800E-06 /K
Aluminum (6061) 75.000E+09 Pa 0.330 2.700E+03 kg/m3 50.000E+06 Pa 23.500E-06 /K
Aluminum (7075) 75.000E+09 Pa 0.330 2.800E+03 kg/m3 95.000E+06 Pa 23.200E-06 /K
Titanium (Ti-17) 115.000E+09 Pa 0.330 5.130E+03 kg/m3 1.050E+09 Pa 8.600E-06 /K
Titanium (Ti-6211) 110.000E+09 Pa 0.310 4.940E+03 kg/m3 730.000E+06 Pa 9.200E-06 /K
Magnesium Alloy 44.000E+09 Pa 0.350 1.920E+03 kg/m3 20.000E+06 Pa 25.000E-06 /K
1 kg
X -0.090359 m
Y 0.0048751 m
Z 0.11001 m
Single Draw
Split Draw
Extrusion
Symmetric
Cyclic
Cyclic Symmetric



Run/Show Analysis Results

Run/Show Optimisation Results

Static analysis



Topological optimisation





Show/Hide

Store/Recall Views

Switch to Perspective Projection

Rotate to closest principal axes

Fit Selected (f)

Add/Edit Section cuts



Workshop

Topolical optimisation
of a
Cantilever beam

width 10 mm x height 20 mm x length 100 mm
Steel AISI 304 (E = 195.10^9 N/m^2)
Support fixed
Force = 100 N
Mesh size = default value

Theoretical Beam deflection : without shear effect
d = F.l^3 / 3EI = 100.0,1^3 / (3.195.10^9.(10.20^3)/12) = $3,08.10^{-4}$ mm
Finite Element deflection : with shear effect, d = $2,65.10^{-2}$ mm


Rectangle by Corners
Points/Lines
Rectangles
Circles
Arcs
Trim/Break
Patch
Create
New Part
Transfer Sketch
Convert Lines
New Plane
Move Plane
Options


0.010 m
End, Int
0.020 m


Trim/Break
Patch
PolyNURBS
Push/Pull
Mirror
Scale
Boolean Modify
Cut
Simplify
Midsurface



With default values **-> deflection = 2,65.10^{-2} mm**



With default values



Évolution of topology



PolyNURBS solution **-> export to STEP file**



PolyNURBS solution **-> deflection = 5,58.10^{-2} mm**



Main steps

With default values



deflection = 2,65.10^{-2} mm



Topological optimisation



PolyNURBS -> STP file



deflection = 5,58.10^{-2} mm


Modèle-poutre1.stmod - solidThinking Inspire 2016
File Edit View Geometry Structure
Files Measure Move
Home
Points/Lines Rectangles Circles Arcs
Create
Trim/Break Patch PolyNURBS
Push/Pull Mirror Scale Boolean Cut Simplify Midsurface
Modify
Create Wrap +/- Loop Bridge Sharpen
Model Browser
Object Mass
Modèle-poutre1 0.007...
Pièce 1 0.0078...
Pièce 1
Max Stiffness Mas...
PolyNURBS Block 5 0 kg
Load Cases
Cas de chargement 1
Property Editor
Name Value
Y
X
Z
vendredi 3 mars 2017
09:28
03/03/2017


Modèle-poutre1.stmod - solidThinking Inspire 2016
File Edit View Geometry Structure
Files Measure Move
Home
Points/Lines Rectangles Circles Arcs Trim/Break Patch PolyNURBS
Create
Push/Pull Mirror Scale Boolean Cut Simplify Midsurface
Modify
Model Browser
Object Mass
Modèle-poutre1 0.067...
Pièce 1 0.0078...
Pièce 1
Max Stiffness Mas...
PolyNURBS Block 5 0.0597...
Load Cases
Cas de chargement 1
Property Editor
Name Value
Y
X
Z


File Edit View Geometry Structure
Files Measure Move
Home
Fasteners Joints Contacts
Connections
Loads Disps Accels Temps Materials Masses Shape Controls
Setup
Analyze Optimize
Run
Model Browser
Object Mass
Modèle-poutre1 0.081...
Pièce 1 0.0215...
Pièce 1
Max Stiffness Mas...
PolyNURBS Block 5 0.0597...
Load Cases
All Loads and Displaceme...
Support 2
Support 3
Force 3
Force 1
Support 1
Cas de chargement 1
Support 2
Support 3
Force 3
Force 1
Support 1
Property Editor
Name Value
Analysis Explorer
Run:
Modèle (1)
Modèle-poutre (2)
Modèle-poutre Max Stiffness Mas...
Modèle-poutre1 (5)
Load Case:
Cas de chargement 1
Result Types:
Displacement
Factor of Safety
Percent of Yield
Tension/Compression
Max Shear Stress
von Mises Stress
Major Principal Stress
Displacement:
Max: 2.042e-005 m
3.766e-007 m
3.390e-007 m
3.013e-007 m
2.636e-007 m
2.260e-007 m
1.883e-007 m
1.507e-007 m
1.130e-007 m
7.533e-008 m
3.766e-008 m
1.476e-015 m
Min: 0.000e+000 m
Animation:
Show:
Callouts:
Min/
Max
Compare Results


Modèle-poutre1.stmod - solidThinking Inspire 2016
File Edit View Geometry Structure
Files Measure Move
Home
Points/Lines Rectangles Circles Arcs Trim/Break Patch PolyNURBS
Create
Push/Pull Mirror Scale Boolean Cut Simplify Midsurface
Modify
Model Browser
Object Mass
Modèle-poutre1 0.081...
Pièce 1 0.0215...
Pièce 1
Max Stiffness Mas...
PolyNURBS Block 5 0.0597...
Load Cases
All Loads and Displaceme...
Support 2
Support 3
Force 3
Force 1
Support 1
Cas de chargement 1
Support 2
Support 3
Force 3
Force 1
Support 1
Section Planes
Section Plane 1
Property Editor
Name Value
General
Name Section Plane 1
Clipping o... One-Sided
Appearance
Visible
Y
X
Z
Section Planes
Section Plane 1


Y
X
Z
Section Planes
Section Plane 1

SOLIDTHINKING INSPIRE 2017

THE INSPIRE 2017 WORKFLOW

Generating the ideal part concept in Inspire is quick and easy. View the Inspire 2017 workflow below. Click on each step to see a quick video demo.



Sketch or Import a Part



Defeature the Part

Define Fasteners, Joints, and Contacts



Assign Materials and Loads

Generate Ideal Shape



Refine using PolyNURBS or Export to CAD



Verify Performance

Manufacture

Source : http://www.solidthinking.com/inspire2017.html

Workshop

1- CAD (presentation)
2- Topological optimisation
3- stl file slicing



Seller :

Stéphane Klein
Directeur administratif et financier
iLoos informatique Strasbourg
s.klein@iloos-informatique.fr

HITEKS
Le Valparc, 18 rue du Parc
67205 OBERHAUSBERGEN
03 90 41 06 60

Groupe iLoos Informatique - Une équipe au service de votre entreprise

STRASBOURG - COLMAR - MULHOUSE - BELFORT - BESANÇON

zortrax M200®


logo_ESIPAP1.stl - Z-Suite v1.7.1
Z-SUITE
MODEL
LIBRARY
Login or Register
POWERED BY zortrax
MODEL
VIEW
TOOLS
SAVE PROJECT
PRINT
Zortrax M200
FR
16:54
02/03/2017


logo_ESIPAP1.stl - Z-Suite v1.7.1
Z-SUITE
MODEL
LIBRARY
Login or Register
POWERED BY zortrax
VIEW
PAUSE
0%
INSERT
Remove All
TOOLS
BACK
SAVE TO PRINT
Profile: Z-ULTRAT
Layer: 0.19mm
Infill: High
Support: 20°
Estimated print time: 0h 25m
Filament usage: 3.22m (8g)
FR
16:44
02/03/2017


logo_ESIPAP1.stl - Z-Suite v1.7.1
Z-SUITE
MODEL
LIBRARY
Login or Register
POWERED BY zortrax
VIEW
PAUSE
1%
INSERT
Remove All
TOOLS
BACK
SAVE TO PRINT
Profile: Z-ULTRAT
Layer: 0.19mm
Infill: High
Support: 20°
Estimated print time: 0h 30m
Filament usage: 3.36m (8g)
FR
16:44
02/03/2017


logo_ESIPAP1.stl - Z-Suite v1.7.1
Z-SUITE
MODEL
LIBRARY
Login or Register
POWERED BY zortrax
VIEW
PAUSE
22%
INSERT
Remove All
TOOLS
BACK
SAVE TO PRINT
Profile: Z-ULTRAT
Layer: 0.19mm
Infill: High
Support: 20°
Estimated print time: 1h 21m
Filament usage: 6.41m (15g)
FR
16:45
02/03/2017


logo_ESIPAP1.stl - Z-Suite v1.7.1
Z-SUITE
MODEL
LIBRARY
Login or Register
POWERED BY zortrax
VIEW
TOOLS
PAUSE
63%
INSERT
Remove All
BACK
SAVE TO PRINT
Profile: Z-ULTRAT
Layer: 0.19mm
Infill: High
Support: 20°
Estimated print time: 2h 58m
Filament usage: 11.53m (27g)
FR
16:46
02/03/2017


logo_ESIPAP1.stl - Z-Suite v1.7.1
Z-SUITE
MODEL
LIBRARY
Login or Register
POWERED BY zortrax
VIEW
TOOLS
PAUSE
85%
INSERT
Remove All
BACK
SAVE TO PRINT
Profile: Z-ULTRAT
Layer: 0.19mm
Infill: High
Support: 20°
Estimated print time: 4h 2m
Filament usage: 14.08m (34g)
FR
16:47
02/03/2017


logo_ESIPAP1.stl - Z-Suite v1.7.1
Z-SUITE
MODEL
LIBRARY
Login or Register
POWERED BY zortrax
VIEW
PAUSE
100%
INSERT
Remove All
TOOLS
BACK
SAVE TO PRINT
Profile: Z-ULTRAT
Layer: 0.19mm
Infill: High
Support: 20°
Estimated print time: 4h 40m
Filament usage: 15.31m (36g)
FR
16:48
02/03/2017



Workshop

1- CAD (presentation)
2- Topological optimisation
3- stl file slicing

ON YOUR DESKTOP

Makerbot Desktop 3.7





Makerbot Replicator 2X

Seller :

Stéphane Klein
Directeur administratif et financier
iLoos informatique Strasbourg
s.klein@iloos-informatique.fr

HITEKS
Le Valparc, 18 rue du Parc
67205 OBERHAUSBERGEN
03 90 41 06 60

Groupe iLoos Informatique - Une équipe au service de votre entreprise

STRASBOURG - COLMAR - MULHOUSE - BELFORT - BESANÇON


MakerBot*
File Edit View Devices Services Help
MakerBot
Explore
Library
Prepare
Store
Learn
logo_ESIPAP1
SETTINGS
esipap
MakerBot
Replicator 2X


MakerBot*
File Edit View Devices Services Help
MakerBot
Explore
Library
Prepare
Store
Learn
logo_ESIPAP1
SETTINGS
ADD FILE
UPLOAD TO LIBRARY
EXPORT PRINT FILE
PRINT
Object Information
logo_ESIPAP1
Extruder:
Left
Extruder to use on a dual extrusion bot
Select All
esipap
MakerBot
Replicator 2X
FR
10:50
06/03/2017

Makerbot Desktop 3D printing settings



Makerbot Desktop 3D printing custom settings



Makerbot Desktop 3D printing custom settings



Makerbot Desktop
3D printing custom settings



Makerbot Desktop 3D printing custom settings



Makerbot Desktop 3D printing exportation



⇒ **.x3g**
Makerbot Replicator 2X specific file exporting

Makerbot Desktop 3D printing printing preview



Makerbot Desktop
3D printing printing preview
First specific layers



General FDM 3D printing run problems
some solution

Incomplete bottom layer -> add additionnal bottom layers

Hanging strands -> change layer thickness and cooling (fan or ambiant temperature)

Too small holes -> use offsets

Burn marks on model -> clean or change nozzle

Irregular walls or material deficiency -> clean, change extruder cable or PCB, or change extruder

Layer shifting during print -> tighten screws on polleys

Unfinished part -> possible problem origins = material tangled u on spool, material running out or material blocked in the extruder

Extrusion problem -> change extruder cable, or change thermocouple and heater

Wraping (raft doesn't stick to the platform) -> adjust distance between nozzles

Delamination of layers (layers split apart)
-> use material with low shrinkage level, print at a temperature more than 20°C.

www.cnrs.fr
IN2P3
http://institut.in2p3.fr/

IPHC
Institut Pluridisciplinaire Hubert Curien
STRASBOURG
http://www.iphc.cnrs.fr/

7- Conclusion

6- Conclusion

1- Complementary manufacturing processes : machining and 3D printing

2- New items in 3D prining :
CAD, STL and AMF file format, design, topological and process optimisation, Finite Element simulations, Slicing, printing settings, safety, file protection,

3- New Additive Manufacturing machines with increased performances, new materials (plastic or metallic) and New services

Thanks for attention !

Source : http://www.ufunk.net/en/techno/3d-printed-flowers/

Source : http://www.123inspiration.com/3d-printed-architectural-structure-by-digital-grotesque/