**CEC-ICMC 2019 - Abstracts, Timetable and Presentations** 



Contribution ID: 1110

Type: Contributed Oral Presentation

## M1Or2A-05: Workability and recrystallization behavior of Nb-Ta, and Nb-Ta-Hf alloys

Monday 22 July 2019 12:00 (15 minutes)

Recent advances in Nb3Sn to meet the very demanding FCC specification of Jc greater than 1500A/mm2 (4.2K, 16T) has led to the development of an Nb-Ta-Hf alloy, which has indicated high layer Jc's of 3700A/mm2 are possible. This high Jc translates to a non-Cu Jc of 2200A/mm2 in an RRP® configuration. The reason for this high Jc (16T,4.2K) is because the irreversibility field of (Nb-Ta)3Sn is unaffected due to the additions of Hf to an Nb-Ta alloy and due to the formation of ultra-fine grain (UFG) Nb3Sn. The mechanism of formation of UFG Nb3Sn is intricately related to microstructure in the Nb-Ta-Hf alloy during the reaction heat treatment stages. To realize the promise of Hf additions, and make a magnet conductor workability of Nb-Ta-Hf up to large strains needs investigation. In this study we investigate the workability of Nb-Ta-Hf restack multifilaments to true strains beyond 10, and compare them with the base Nb-Ta alloy. Given the relevance of the microstructure in the alloy rod during the Nb3Sn reaction we also compare the recrystallization behavior of the heavily drawn Nb-Ta, and Nb-Ta-Hf conductors. Results of multi-filament conductor drawing have been performed up to a strain of 7, and no intermediate breaks have been observed. Recrystallization behavior of Nb-Ta-Hf alloy at a strain of 7 indicates significant grain growth occurs only beyond 750°C, whereas grain growth is observed at 600°C in the corresponding Nb-Ta conductors.

**Authors:** WALKER, Benjamin (Department of Mechanical Engineering); Dr BALACHANDRAN, Shreyas (National High Field Magnet Laboratory); STARCH, William L. (National High Magnetic Field Laboratory, Florida State University); LEE, Peter (Florida State University); TARANTINI, Chiara (FSU); LARBALESTIER, David (National High Magnetic Field Laboratory)

Presenter: WALKER, Benjamin (Department of Mechanical Engineering)

Session Classification: M1Or2A - A15 Conductors