

Count	Thickness, mm	Weight, g	Density, g/cm ³	Coating	Extremity	Type
1	23.6	740.1	1.74	yes	no	Spongy
2	23.6	736.6	1.73	yes	no	Spongy
3	23.6	744	1.75	yes	no	Spongy
4	23.6	743.6	1.75	yes	no	Spongy
5	23.6	732.3	1.72	yes	no	Spongy
6	23.6	738.6	1.74	yes	no	Spongy
7	23.6	754.3	1.78	yes	no	Woody
1	23.7	581.3	1.36	yes	no	Woody
2	23.7	602.2	1.41	no	no	Spongy
3	23.7	622.7	1.46	no	no	Spongy
4	23.7	634.8	1.49	no	no	Spongy
5	23.7	618.5	1.45	no	no	Spongy
6	23.7	630.8	1.48	no	no	Spongy
7	23.7	628.2	1.47	no	no	Spongy
8	23.7	620.3	1.45	no	no	Spongy
9	23.7	616	1.44	no	no	Spongy
10	23.7	645.7	1.51	no	no	Spongy
11	23.7	625.4	1.47	no	no	Spongy
12	23.7	652.1	1.53	no	no	Spongy
13	23.7	633.2	1.48	no	no	Spongy
14	23.7	640.4	1.50	no	no	Spongy
1	23.8	615.6	1.44	yes	yes	Woody
2	23.8	627.2	1.46	yes	no	Woody
3	23.8	609.6	1.42	no	yes	Spongy
4	23.8	600.4	1.40	no	yes	Spongy
5	23.8	589.6	1.38	no	yes	Spongy
6	23.8	604.4	1.41	no	yes	Spongy
7	23.8	611.6	1.43	no	no	Spongy
8	23.8	628.6	1.47	no	no	Spongy
9	23.8	614.3	1.43	no	no	Spongy
10	23.8	623.2	1.45	no	no	Spongy
11	23.8	659	1.54	no	no	Spongy
12	23.8	650.8	1.52	no	no	Spongy
13	23.8	650.1	1.52	no	no	Spongy
14	23.8	656.3	1.53	no	no	Spongy
15	23.8	612.6	1.43	no	no	Spongy
16	23.8	619.1	1.45	no	no	Spongy
1	23.9	751.1	1.75	yes	no	Spongy
2	23.9	749.5	1.74	yes	no	Spongy
3	23.9	739	1.72	yes	yes	Spongy
4	23.9	740.4	1.72	yes	yes	Spongy
5	23.9	749.4	1.74	yes	yes	Woody
6	23.9	736	1.71	yes	no	Woody
1	40	1015.7	1.41	no	no	Spongy
2	40	1208.8	1.68	no	no	Spongy

The 23.9 thickness have been removed from a TCDS in March 2006; the density of the blocks marked "Extremity" does not take into account the slightly reduced volume due to the tapering.